

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
0-Chloro Napthalene	B	A		A				
1 Dodecanol, pure - Alcohol, Aliphatic	X							
1 Hexadecanol, pure- Alcohol, Aliphatic	B							
1 Propanol, 100% - Alcohol, Aliphatic	B							
1 Propanol, pure - Alcohol, Aliphatic	B							
1, 2- ethanediol, 30% - Alcohol, Aliphatic, Polyol	B							
1, 2- ethanediol, pure - Alcohol, Aliphatic, Polyol	B							
1, 2, 2, 2- Tetrafluoroethane, pure - Hydrocarbon, Aliphatic, Halogenated	X							
1, 3- Benzenediol, 5% - Alcohol, Aromatic, Polyol	B							
1, 3- Benzenediol, pure - Alcohol, Aromatic, Polyol	B							
1, 3- Benzenediol, saturated - Alcohol, Aromatic, Polyol	B							
1, 3- Butylene Glycol, pure - Alcohol, Aliphatic, Polyol	X							
1, 4- Benzoquinone, pure - Ketone, Aliphatic, Cyclic	X							
1, 4-Dioxane	A							
2-Butoxyethanol, pure - Ether, Aliphatic, Alcohol	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
2-Mercaptoethanol, pure - Alcohol, Aliphatic, Mercaptan	X							
2-Methoxyethanol, pure - Ether, Aliphatic, Alcohol	C							
2-Methoxyethanol Acetate, pure - Ether, Aliphatic, Ester	C							
2-Propanol, 100% - Alcohol, Aliphatic	B							
2-Propanol, 30% - Alcohol, Aliphatic	B							
2, (2-Ethoxyethoxy) ethano, pure - Ether, Aliphatic, Alcohol	B							
2, 4, 6 - Trimethyl-1, 3, 5-tioxane, pure - Ketone, Aliphatic, Cyclic	X							
3-Pentanone, pure - Ketone, Aliphatic	C							
4-Hydroxy-4-methyl-2-pentanone, pure - Ketone, Aliphatic, Alcohol	B							
9-Octa Decanoic Acid								
9.12 Octadecadienoic Acid								
Abietic Acid	X							
Acetaldehyde	A	A				A	C	C
Acetaldehyde-100% aq sol-68F	A	A						
Acetaldehyde-40% aq sol-68F	A	A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Acetamide	A	B				A	B	B
Acetamide, - 25%	A	A				A	B	B
Acetamide, Powder								
Acetanilide	B							
Acetate Solv.	B	A						
Acetates	B	A						
Acetic Acid-85%	A	A						
Acetic Acid	A	A						
Acetic Acid - Glacial	A	A				A	C	C
Acetic Acid 10%	A			A	A	A		
Acetic Acid 20%	A	A		B	B	A		
Acetic Acid 30% 5.4 BE	A			C	C	A	A	A
Acetic Acid 33%	A			A	X	A		
Acetic Acid-100% Un aerated	A	A						
Acetic Acid-100% Un aerated-Boiling	B	B						
Acetic Acid-100%-70F	B	B						
Acetic Acid-100%-Boiling	B	B						
Acetic Acid-20% Un aerated	A	A						
Acetic Acid-20%-70F	A	B	X					
Acetic Acid-5% Un aerated	A	A	X					
Acetic acid-50% Un aerated	B	A	X					
Acetic acid-50% Un aerated-Boiling	B	B	X					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Acetic Acid-50%-70F	B	B	X					
Acetic Acid-50%-Boiling	B	B	X					
Acetic Acid-60%	B	A	X					
Acetic Acid-80%-70F	B	B	X					
Acetic Acid-80%-Boiling	B	B	X					
Acetic Acid, <5% - Acid, Organic	A		X					
Acetic Acid, 1% - Acid, Organic	A		X					
Acetic Acid, 10% - Acid, Organic	A		X					
Acetic Acid, 100% - Acid Organic	B		X					
Acetic Acid, 25% - Acid, Organic	B		X					
Acetic Acid, 30%	A		X					
Acetic Acid, 50% - Acid, Organic	B		X					
Acetic Acid, 60% - Acid, Organic	B		X					
Acetic Acid, 80%	B	A	X					
Acetic Acid, 90% - Acid, Organic	B		X					
Acetic Acid, Glacial	X	A	X	A				
Acetic Acid, Glacial - Acid, Organic	B		X					
Acetic Aldehyde	A	C						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Acetic Anhydride-100% -70F	A		X	A	A		A	A
Acetic anhydride-68F	A		X	A	A	B	A	A
Acetic Anhydride-90%-70 F	A	B	X				A	A
Acetic Anhydride-90%- Boiling	A	B	X					
Acetic Anhydrite	X	A	X					
Acetone -100%-68F	A	B	X	A	C	C	B	B
Acetone -100%-70F	A	B	X	A	C	C	B	B
Acetone -50% Water	A	B	X			B	A	A
Acetone -Boiling	A	B	X			C		
Acetone -Traces-68F	A	A	C			B	A	A
Acetone Cyanohydrin	A							
Acetonic								
Acetonitrile	A	A				C		
Acetophenone	B	X				A	X	X
Acetotoluidide	C							
Acetyl Acetone	E							
Acetyl Benzene								
Acetyl Bromide	B							
Acetyl Chloride	XA	A					X	X
Acetyl Chloride- Cold & Boiling		B						
Acetyl Chloride-Dry	A	A						
Acetylene	A	A					B	B

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Acetylene-70F	A	B				A		
Acetylene DI + Tetra Chloride	X							
Acetylene-Gas 100%		A						
Acetylsalicylic Acid	C							
Acidic Cleaning Solution - Detergent	X							
Acids, Non-organic	X							
Acids, Organic	X							
Acohol, Methyl-150F		B						
Acohol, Methyl-70F		B						
Aconitic Acid	X							
Acridine	X							
Acrolein	A							
Acrylamide, pure - Misc.	B							
Acrylic Acid	A							
Acrylic Acid- 97%	A			A		A		
Acrylic Aldehyde								
Acrylonitrile	X	C		B	C	X	C	C
Adipic Acid		A						
Adipic Acid (Adipinic Acid)		A						
Adipic Acid-Sat'd		A						
Air								
Air 400 - 500° F	C							
Air Below 200° F	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Aliphatic Dicarboxylic Acid	C							
Aliphatic Hydrocarbon								
Aliphatic Hydrocarbons-68F								
Aliphatic Naphtha								
Alk-Tri								
Alkaform		A						
Alkaline Sucrose - Misc.	B							
Alkanes								
Alkanesulfonic Acid	C							
Alkazene							X	X
Alkenes (Olefin Hydrocarbons)	C							
Alkyl Acetone	B							
Alkyl Alcohol	C							
Alkyl Amine	C							
Alkyl Aryl Sulfonates	C							
Alkyl Aryl Sulfonics	C							
Alkyl Benzene	C							
Alkyl Chloride	C							
Alkyl Sulfide	C							
Alkylnaphthalene Sulfonic Acid	C							
Allomaleic Acid								
Allyl Alcohol-96%	A/B	A				A/B		

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Allyl Chloride	B							
Allyl Alcohol	A							
Allyl Aldehyde								
Allyl Bromide								
Allyl Chloride		A						
Allyl Chloride-68F		A						
Allyl Phenyl Methyl Ether								
Allyl Trichloride								
Allylidene Diacetate	B							
Almond Oil.Artificial								
Aloin (Powder)								
Alpha Chloropropylene								
Alpha Chlorotoluene								
Alpha Hydroxtoluene								
Alpha Picoline	B							
Alum	A	A	A			A		
Alum (Also see Type)	A		A					
Alum Potassium Sulfate (Alum), 10%								
Alum Potassium Sulfate (Alum), 100%		A						
Alum, 5% - Salt, Inorganic	A							
Alum, pure - Salt, Inorganic	B							
Aluminum Acetate	A					A	B	B

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Aluminium Chloride-68F	A	C	A	A	A	A	A	A
Aluminium Fluoride-68F	A		A			A	A	A
Aluminium Hydroxide-68F	A		A	A	A			
Aluminium Nitrate-68F	A		A	A	A	A	A	A
Aluminium Oxychloride-68F			A					
Aluminium Sulphate-68F	A	C						
Aluminum Acetate-Saturated-70F		B						
Aluminum Acetate-Sat'd		A						
Aluminum Acetate-Saturated-Boiling		B						
Aluminum Ammonium Sulfate (Alum)- Sat'd		A						
Aluminum Bromide				A	A			
Aluminum Chlorate	B							
Aluminum Chloride	A	C	A	A	A	A		
Aluminum Chloride 20%	A	C	A					
Aluminum Chloride Aqueous-Sat'd	A	A	A					
Aluminum Chloride-5%		X						
Aluminum Ethylate	X							
Aluminum Fluoride		C		A	A	A		
Aluminum Fluoride Anhydros-Sat'd		C						
Aluminum Fluoride-5%		B						
Aluminum Fluorosilicate	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Aminoisobutyric-2-Acid								
Aminodimethylbenzene	B							
Aminoethane	A							
Aminopyridine	X							
Aminosalicylic Acid	X							
Aminoxilene	B							
Ammono-Phos								
Ammonia	A	A	A	A	A	A		
Ammonia -Crystal								
Ammonia (Anhydrous-Dry)		A				a	A	A
Ammonia (Dry & Moist)-All Concentrations		B					A	A
Ammonia (Dry & Moist)-Anhydrous-70F		B					A	A
Ammonia (Dry & Moist)-Anhydrous-Hot F		C					A	A
Ammonia 10%	A	A		A	A	A	A	A
Ammonia Acetate-Sat'd		C	A					
Ammonia Alum								
Ammonia and Lithium Metal in Solution								
Ammonia Anhydrous	A	A		A	A	A		
Ammonia Bifluoride		A						
Ammonia Bisulfite				A	A	A		
Ammonia Carbonate			A					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ammonia Chloride			A					
Ammonia Cupric Sulfate								
Ammonia Gas (cold)			A			a	A	A
Ammonia Gas (Hot)			A			b	B	B
Ammonia Gas-100%		A	A					
Ammonia Liquid-100%		A	A					
Ammonia, 25% - Base/Caustic, Inorganic	B					A		
Ammonia, Anhydrous	A	A						
Ammonia, Liquid (Anhydrous)	B					A		
Ammonia, Liquids	B	A						
Ammonia, Nitrate		A	A					
Ammonium -Bifluoride		B						
Ammonium -Bisulfide								
Ammonium Carbonate	A					a	A	A
Ammonium -Chloride-Sat'd	A	C					A	A
Ammonium -Dichromate								
Ammonium -Fluoride-10%		X						
Ammonium -Fluoride-25%		X						
Ammonium Acetate		A						
Ammonium Alum		A						
Ammonium Alum (Slightly Ammoniacal)		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ammonium Aluminum Sulfate								
Ammonium Arsenate	B	B						
Ammonium Benzoate	B	B						
Ammonium Bicarbonate	B	B						
Ammonium Bifluoride (Saturated)								
Ammonium Bifluoride-10%								
Ammonium Bromide								
Ammonium Bromide-5%		A						
Ammonium Carbamate	B							
Ammonium Carbonate		A	A					
Ammonium Carbonate-1% and 5%-70F		B	A					
Ammonium Carbonate-Aerated-70F		B	A					
Ammonium Carbonate-All Conc.-Hot&Cold	A	A	A					
Ammonium Carbonate-Aq.-Any Conc.-70F	A							
Ammonium Carbonate, Saturated	A	C						
Ammonium Casenite		A						
Ammonium Chloride	A	C	A	A	A	a		
Ammonium Chloride-1%	A	A	A			a		
Ammonium Chloride-1% -70F	A	B	A					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ammonium Chloride-1% /28%/50%-Boiling	A	B	A					
Ammonium Chloride-10%- Boiling	A	A	A					
Ammonium Chloride-28%- Boiling	A	A	A					
Ammonium Chloride-50%- Boiling	A	A	A					
Ammonium Chloride, 2N	A		A					
Ammonium Chromic Sulfate								
Ammonium Citrate	B							
Ammonium Dichromate								
Ammonium Diphosphate								
Ammonium Flouride				A	A			
Ammonium Flouride-68F								
Ammonium Fluoride Acid								
Ammonium Fluorosilicate	X							
Ammonium Formate	B							
Ammonium Glycolate, pure - Salt, Inorganic, Amine	A							
Ammonium Hydrate-38%								
Ammonium Hydrogen Fluoride								
Ammonium Hydrosulphide-68F								
Ammonium Hydrox	A	A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ammonium Hydroxide	A	A		A	A	a	A	A
Ammonium Hydroxide Concentrated	A	A						
Ammonium Hydroxide-10%	A	A						
Ammonium Hydroxide-68F	A	A						
Ammonium Hydroxide-70F	A	B						
Ammonium Hydroxide, 10% - Base/Caustic, Inorganic	A							
Ammonium Hydroxide, 1N - Base/Caustic, Inorganic	A							
Ammonium Hydroxide, 25% - Base/Caustic, Inorganic	A							
Ammonium Hydroxide, 28% - Base	A							
Ammonium Hydroxide, 3 Molar	A							
Ammonium Hydroxide, 3 Molar								
Ammonium Hydroxide, 30% - Base/Caustic, Inorganic	A							
Ammonium Hydroxide, 5% - Base/Caustic, Inorganic	A							
Ammonium Hydroxide, 6% - Base/Caustic, Inorganic	A							
Ammonium Hydroxide, 6N - Base/Caustic, Inorganic	A							
Ammonium Hydroxide, pure - Base/Caustic, Inorganic	A							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ammonium Oxolate-5% -70F		B						
Ammonium Perchlorate	B							
Ammonium Perchlorate- 5%-70F		B						
Ammonium Perchloride	X							
Ammonium Persulfate		A		A	A	A	A	A
Ammonium Persulfate- 10%						A	A	A
Ammonium Persulfate- Solution							A	A
Ammonium Persulphate- 5%		A					A	A
Ammonium Persulphate- 5%-70F		B					A	A
Ammonium Phosphate - 5%	A	A	A			A	A	A
Ammonium Phosphate - 68 F	A		A			A	A	A
Ammonium Phosphate - Saturated-70F	A	B	A			A	A	A
Ammonium Phosphate -5%-70F	A	B	A			A	A	A
Ammonium Phosphate, Dibasic	A	A	A					
Ammonium Phosphate, Monobasic		A						
Ammonium Phosphate, Tribasic		B						
Ammonium Phosphite	B							
Ammonium Picrate	B							
Ammonium Polysulfide	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff);</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ammonium Rhodanate								
Ammonium Salicyclate	B							
Ammonium Salts	A							
Ammonium Sulfamate	B							
Ammonium Sulfate	A	C	A				A	A
Ammonium Sulfate -Aq.- Any Conc.-70F	A		A					
Ammonium Sulfate Nitrate	B							
Ammonium Sulfide	A			A	A			
Ammonium Sulfide-Dilute	A	C						
Ammonium Sulfite	A	B						
Ammonium Sulphate	A		A					
Ammonium Sulphate-1% and 5%-70F	A	B	A					
Ammonium Sulphate-1% and 5%-Agitated Ae	A	A	A					
Ammonium Sulphate-10% -Boiling	A	B	A					
Ammonium Sulphate-10% -Boiling	A	A	A					
Ammonium Sulphate- Saturated-Boiling	A	B	A					
Ammonium Sulphide-68F								
Ammonium Sulphite-70F		B						
Ammonium Sulphite- Boiling		B						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ammonium Sulphite-Saturated-Cold&Boiling		A						
Ammonium Thiocyanate								
Ammonium Thiocyanate-50-60%		A						
Ammonium Thioglycolate	B							
Ammonium Thiosulfate	A	A						
Ammonium Tribasic		A						
Ammonium Tungstate	B							
Ammonium Valerate	B							
Amyl Acetate	A	A				A	X	X
Amyl Acetate-Concentrated-70F	X	B					X	X
Amyl Alcohol	A	A	C	A	C	A	A	A
Amyl Borate						X	A	A
Amyl Butyrate	C							
Amyl Chloride	X	B						
Amyl Cinnamic Aldehyde	C							
Amyl Laurate	C							
Amyl Napthalene						X	X	X
Amyl Mercaptan	C							
Amyl Nitrate	B							
Amyl Nitrite	B							
Amyl Propionate	C							
Anethole	C							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Aniline	A	A	X			B	C	C
Aniline Hydrochloride		X				B	X	X
Aniline Hydrochloride-5%		X				B		
Aniline Hydrochloride-68F						B		
Aniline Hydrochloride-70F		C				B		
Aniline Hydrochloride- Sat'd		X						
Aniline Sulfate	B							
Aniline Sulfite	B							
Aniline-3%-70F		B						
Aniline-68F	A							
Aniline-Conc.	A	A						
Aniline-Conc. Crude-70F	A	B						
Aniline Dyes	A							
Aniline Oil	B							
Animal Fats	A	A				b		
Animal Gelatin								
Animal Glue	A	A						
Animal Oils (Lard Oil)	A	A					B	B
Anisole	X							
Anisoyl Chloride	X							
Ansul Ether						C		
Anthracene	C							
Anthranilic Acid	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Anti-Freeze	A	A	A	A	A	A		
Antichlor								
Antimonic Chloride								
Antimonous Chloride								
Antimony Chloride-68F								
Antimony Chlorides								
Antimony Pentachloride	A							
Antimony Pentafluoride	X							
Antimony Salts	A							
Antimony Sulfate	X							
Antimony Tribromide	C							
Antimony Trichloride	A	X						
Antimony Trichloride -70F		C						
Antimony Trichloride-Sat'd		X						
Antimony Trifluoride	C							
Antimony Trioxide	C							
Antimony-Molten		C						
Aqua Regia (80%HCl, 20% HNO)	B	X	X			C		
Arochlor 1248		B				C	X	X
Aromatic Hydrocarbons		A					X	X
Argon	A							
Argon-Dry	A	A						
Arquads						A		

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Arsenic Acid	B	A	A			A	A	A
Arsenic Acid-150F	B	B	A			A	A	A
Arsenic Acid-80%	B	A	A			A	A	A
Arsenic Acid-90%-225F	B	B	A			A	A	A
Arsenic Oxide	X							
Arsenic Salts	A							
Arsenic Trichloride							A	A
Arsenic Trioxide	X							
Arsenic Trisulfide	C							
Arsenites	X							
Arsine	X							
Aryl Orthosilicate	X							
Aryl Sulfonic Acid								
Ascorbic Acid	X							
Askarel						X	X	X
Aspartic Acid	B							
Asphalt	B	A	C			X	C	C
ASTM Method D-471, 1								
ASTM Oil, No.5	C							
ASTM Reference Fuel D	C							
ASTM-Ref: Fuel A	B							
ASTM-Ref: Fuel B	B							
ASTM-Ref: Fuel C	C							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
ASTM#1 Oil	A	A						
ASTM#2 Oil	A	A						
ASTM#3 Oil	B	A						
Astral Oil								
Asymmetrical Trimethylbenzene, pure - Hydrocarbon, Aromatic	C							
ATL-857								
Atlantic Ulro Gear-e	C							
Atlantic Ulro Gear-EP Lube								
Aure 903R (Mobil)	C							
AUREX 256	X							
Automatic Transmission Fluid	B					A		
Automotive Brake Fluid	B					C		
Aviation Gasoline	A	A				A		
AXAREL 9100	X							
Azobenzene	X							
Baking Oven Gases		A						
Banana Oil	B							
Barium Hydroxide-Sat'd	A	A						
Barium Carbonate		A						
Barium Carbonate-5% to Sat		A						
Barium Carbonate-70F		B						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Barium Carbonate-Sat'd	A	A						
Barium Chlorate	B							
Barium Chloride	A	A		A	A	A	A	A
Barium Chloride-5%-70F	A	B					A	A
Barium Chloride-Aqueous Sol.-Hot	A	A					A	A
Barium Chloride-Sat'd	A	A					A	A
Barium Chloride-Sturated-70F	A	B					A	A
Barium Cyanide		A						
Barium Hydrate-Aqueous Sol.-Hot		A						
Barium Hydroxide	A	A		A	A	A	A	A
Barium Hydroxide-68F	A						A	A
Barium Iodide	B							
Barium Nitrate-Aqueous Sol.-Hot		B						
Barium Nitrate-Sat'd		A						
Barium Oxide	B							
Barium Peroxide	B							
Barium Polysulfide	B							
Barium Salts	A		A					
Barium Sulfate		A				A	A	A
Barium Sulfate-Sat'd		A					A	A
Barium Sulfide	A	A		A	A		A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Barium Sulfide-Sat'd	A	A					A	A
Barium Sulphate		A					A	A
Barium Sulphate -68F							A	A
Barium Sulphate-70F		B					A	A
Barium Sulphide	A						A	A
Barium Sulphide - Saturated-70F	A	B					A	A
Barium Sulphide-68F	A						A	A
Barley-Malt & Hops-70F		B						
Bayol D	C							
Beer	A	A		A	C	A	A	A
Beer Sugar Liquors	A	A				A	A	A
Beer-70F	A	B					A	A
Beet Sugar	A					A	A	A
Beet Sugar Liquids	A	A					A	A
Benzaldehyde	B	A	X			A		
Benzaldehyde Disulfonic Acid	D							
Benzaldehyde-10%	B	A						
Benzaldehyde, pure - Amine, Aromatic	B							
Benzene	B	A	X			X	X	X
Benzene Sulfonic Acid		B					A	A
Benzene Sulfonic Acid- 10%		C					A	A
Benzene-68F	B		X					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Benzene-70F	B	B	X					
Benzenesulfonic Acid, pure - Acid, Organic, Aromatic	B							
Benzidine	C							
Benzidine 3 Sulfonic Acid	C							
Benzil	C							
Benzilic Acid	C							
Benzyl Alcohol						B	A	A
Benzocatechol	C							
Benzochloride								
Benzoic Acid	A	A	A	A	A			
Benzoic Acid-70F	A	B	A					
Benzoic Acid-All Conc.	A	A	A					
Benzoic Acid-Hot	A	A						
Benzol	X	A						
Benzol-70F	X	B						
Benzonitrile		X						
Benzoquinone	C							
Benzotrifluoride	B							
Benzoyl Peroxide	X							
Benzoylsulfonilic Acid	C							
Benzyl Acetate, pure - Ester Aromatic	B							
Benzyl Alcohol	B	A				B	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Benzyl Alcohol -68F						B	A	A
Benzyl Amine	X							
Benzyl Benzoate						B		
Benzyl Bromide	C							
Benzyl Butyl Phthalate	B							
Benzyl Carbinol, pure - Alcohol, Aromatic	X							
Benzyl Chloride		B		A	C		X	X
Benzyl Phenol	C							
Benzyl Salicylate	C							
Beryllium Chloride	B							
Beryllium Fluoride	B							
Beryllium Oxide	B							
Beryllium Sulfate	B							
beta-Mercaptoethanol, pure - Alcohol, Aliphatic, Mercaptan	X							
Biocide		C						
Biodiesel	B	A		A	B	A		
Bis(2-ethylhexyl) Phthalate, pure - Ester, Aromatic	C							
Bismuth Carbonate			A					
Bismuth Carbonate - 68F			A					
Bismuth Nitrate	B							
Bismuth Oxychloride	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Bismuth Subcarbonate								
Bismuthyl Carbonate								
Bittern	X							
Black Ash								
Black Liquor	A			A	A			
Black Liquor-Saturated		A						
Black Sulfate Liquor	A							
Bleach	A	A	A			A	C	C
Bleach -12% Active C12	A	A	A			A		
Bleach (Sodium Hypochlorit 20%)	A	A	A	A	A	A		
Bleach-5% Active C12	A	A	A			A		
Bleaching Liquor	A	A	A					
Bleaching Powder	A	A	A					
Bleaching Powder-Cold	A	A	A					
Blood	A	A						
Blood (Meat Juice)-Cold	A	B						
Blood (Meat Juice)-Fused	A	A						
Bone Oil			C					
Borax	A	A	A			A	A	A
Borax (Sodium Borate)	A	A	A				A	A
Borax Solutions	A	A	A				A	A
Borax-5%-Boiling	A	A	A				A	A
Borax-5%-Hot	A	A	A				A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Borax-Sat'd	A	A	A				A	A
Boric Acid	A	A	A	A	A	A	A	A
Boric Acid -100%-70F	A		A			A	A	A
Boric Acid-5%-Hot	A	A	A			A	A	A
Boric Acid-Dry	A	A	A			A	A	A
Boric Acid-Sat'd	A	A	A			A	A	A
Boric Acid-Saturated-Boiling	A	A				A	A	A
Boric Oxide	B							
Borneol	C							
Bornyl Acetate	C							
Bornyl Chloride	C							
Bornyl Formate	C							
Boron Hydride	X							
Boron Phosphate	X							
Boron Tribromide	X							
Boron Trichloride	X							
Boron Trioxide	X							
Brake Fluid	B					C		
Brake Fluid DOT3 (Glycol Type)	B							
Brake Fluid-70F	B							
Brake Fluid-Automotive	B					C		
Brass Plating, High Speed Brass Bath 110F		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Brass Plating, Regular Brass Bath 100F		A						
Brewery Slop		A						
Brine	A	B		A	A	A	A	A
Brine (Sea Water)	A		A			A		
Brine-Sat'd	A	A	A			A		
Bromacil								
Bromine	A	X					A	A
Bromine (Wet)		X						
Bromine Pentaflouride								
Bromine Triflouride						X	X	X
Bromine Water		A					B	B
Bromine Water-Cold-Sat'd.							B	B
Bromine-100% (dry gas) -68F							B	B
Bromine-70F		C					B	B
Bromine-Liquid		X					B	B
Bromine-Vappor		X					B	B
Bromobenzene	C/X					X	X	X
Bromobenzene Cyanide	B							
Bromochlorometane	B							
Bromomethane	B							
Bromotoluene	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Butanol (Butyl Alcohol)	B	A						
Butyl Acetate	X							
Butyl Acrylate	X							
Butoxyethanol	A							
Butene 2-Ethyl (1-Butene 2-Ethyl)	C							
Butryl Chloride	C							
Butter	X	A				A	B	B
Butter (Animal Fat)								
Buttermilk		A						
Buttermilk -70F		B						
Butyl		A						
Butyl Acetate		C		A	C		X	X
Butyl Acetate Ricinoleate							B	B
Butyl Acetate-100%-70F								
Butyl Acetate-68F								
Butyl Acetate-n	A	C						
Butyl Aceto Acetate								
Butyl Acetyl Ricinoleate								
Butyl Acrylate				A	C			
Butyl Alcohol	A	A	X			A	A	A
Butyl Alcohol (tertiary)	A		X					
Butyl Amine		A					X	X
Butyl Benzolate	B					C	X	X

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Butyl BezyI Phthalate	B							
Butyl Carbitol	C					A	B	B
Butyl Cellosolve	A	A				C	B	B
Butyl Cellosolve Acetate				A	C			
Butyl Chloride	B							
Butyl Ether	B	A						
Butyl Ether Acetaldehyde	B							
Butal Ethyl Ether	B							
Butyl Glycolate	B							
Butyl Lactate	B							
Butyl Laurate	B							
Butyl Mercaptan (Tertiary)	C							
Butyl Methacrylate	B							
Butyl Oleate	B						X	X
Butyl Phthalate	B	B						
Butyl Stearate	B	A				B		
Butylbenzoic Acid	C							
Butylene	C	A					C	C
Butylene - Liquid	C	A				B		
Butylene Glycol, pure - Alcohol, Aliphatic, Polyol	X							
Butyraldehyde, pure - Aldehyde, Aliphatic	A					C	C	C
Butyric Acid	A	A	A					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Butyric Acid 20%	A	A	A					
Butyric Acid-5%	A	A	A					
Butyric Acid-5%-150F	A	B						
Butyric Acid-5%-70F	A	B	A					
Butyric Acid, Aqueous Sol.-Sp.G.964-Boiling		B						
Butyric Anhydride	A							
Butyronitrile								
Cacao Butter								
Cadmium Acetate	A							
Cadmium Chloride				A	A			
Cadmium Cyanide								
Cadmium Nitrate	B							
Cadmium Oxide	B							
Cadmium Plating, Cyanide				A	A			
Cadmium Plating, Cyanide Bath 90F		A						
Cadmium Plating, Fluoborate Bath 100F		A						
Cadmium Sulfide	B							
Cadmium Sulfate	B							
Cadmium-Motten		X						
Cajeputene								
Calcium Acetate	A					B	B	B
Calcium Aluminate	A							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Calcium Arsenate	B							
CAlcium Benzoate	C							
Calcium Bicarbonate	B							
Calcium Bichromate	A							
Calcium Bisulfate		A				A	A	A
Calcium Bisulfide		B				A	A	A
Calcium Bisulfite		A		A	A		A	A
Calcium Bisulphite							A	A
Calcium Bromide	B							
Calcium Carbide	X							
Calcium Carbonate		A						
Calcium Carbonate -68F								
Calcium Carbonate-70F		B						
Calcium Chlorate		A						
Calcium Chlorate-68F								
Calcium Chlorate-Dilute Sol.-Hot		B						
Calcium Chlorate-Dilute- Hot/Cold		A						
Calcium Chloride	A	C	A	A	A	A	A	A
Calcium Chloride (saturated)	A	B					A	A
Calcium Chloride 30% in water	A	B						
Calcium Chloride- Conc. Sol.-70F	A	B						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Calcium Chloride-20% in methyl alcohol-68F	B							
Calcium Chloride-aq. sol. -68F	A							
Calcium Chloride-Dil or Conc.	A	A						
Calcium Chloride-Dilute Sol.-70F	A	B						
Calcium Chloride, Aq., Sat.-70F	A							
Calcium Chromate	B							
Calcium Cyanamide	X							
Calcium Cyanide								
Calcium Flourphosphate								
Calcium Fluoride		B						
Calcium Hydrate								
Calcium Hydride	B							
Calcium Hydrosulfide	B							
Calcium Hydroxide	A	A		A	A		A	A
Calcium Hydroxide (Caustic Lime)	A						A	A
Calcium Hydroxide (saturated)	A	B					A	A
Calcium Hydroxide 10%	A	B					A	A
Calcium Hydroxide-10% to 20%-Boiling	A	A					A	A
Calcium Hydroxide-10%-Boiling	A	B					A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Calcium hydroxide-20%-Boiling	A	B					A	A
Calcium Hydroxide-50%-Boiling	A	B					A	A
Calcium Hydroxide-68F	A						A	A
Calcium Hypochloride	B	B					C	C
Calcium Hypochloride-2% -70F	B	B					C	C
Calcium Hypochlorite	B	C		C	C	C	C	C
Calcium Hypochlorite saturated	B	B					C	C
Calcium Hypochlorite-2%	A	A					C	C
Calcium Hypochlorite-30%	B	C					C	C
Calcium Hypochlorite-68F	B						C	C
Calcium Hypophosphite	B							
Calcium Lactate	B							
Calcium Monoxide								
Calcium Naphthenate	X							
Calcium Nitrate	A	B	A	A	A	A	A	A
Calcium Nitrate-68F	A		A				A	A
Calcium Nitrate, Aq. Sat. -70F	A		A				A	A
Calcium Oxalate	B						A	A
Calcium Oxide		A						
Calcium Oxychloride-15%								
Calcium Permanganate	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Calcium Peroxide	X							
Calcium Phenolsulfonate	B							
Calcium Phospate Acid	B							
Calcium Phosphate								
Calcium Phosphate-68F								
Calcium Propionate	B							
Calcium Pyridine Sulfonate	X							
Calcium Salts	A							
Calcium Silicate								
Calcium Silico-Aluminate								
Calcium Stearate	C							
Calcium Sulfamate	C							
Calcium Sulfate		A		A	A			
Calcium sulphate-Saturated		A						
Calcium Sulphate-Saturated-70F		B						
Calcium Sulfide	A					B	A	A
Calcium Thiocyanate	B							
Calcium Thiosulfate								
Calcium Tungstate	B							
Calcyanide								
Calgon		A						
Caliche								
Camphene	C							

<u>A=Great Application;</u> <u>B=Good Application (mild</u> <u>effect); C=Conditional Use</u> <u>(consult with ES</u> <u>Technical Staff); X=Do</u> <u>Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Camphor		A						
Camphoric Acid	C							
Candol								
Cane Juice		A						
Cane Sugar		A				A	A	A
Capric Acid	C							
Caprillic Acid	B							
Caproic Acid	C							
Caproic Aldehyde								
Caprol Alcohol								
Caprolactam	C							
Capronaldehyde	C							
Caprylic Acid		A						
Carbamate							B	B
Carbamide	A					B		
Carbazole	B							
Carbitol	A	C				B	B	B
Carbolic Acid Phenol	C	B				X	C	C
Carbolic Acid-CP-70F	C	B					C	C
Carbolic Acid-CP-Hot	C	B					C	C
Carbolic Acid, C.P.	C	A					C	C
Carbon Bisulfide		A					X	X
Carbon Bisulphide		A	X			C	X	X

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff);</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Carbon Bisulphide-70F		B	X				X	X
Carbon Dioxide	A	A	A	A	A	A	B	B
Carbon Dioxide (Dry)-70F	A	B		A	A	A	B	B
Carbon Dioxide (Explosive Decompression Use)	B							
Carbon Dioxide (Wet)	A	A		A	A			
Carbon Dioxide-Dry-100%	A	A		A	A			
Carbon Dioxide-Wet	A	A		A	A			
Carbon Dioxide-Wet or Dry	A	A		A	A			
Carbon Disulfide	C	A		A	A			
Carbon Fluorides	C							
Carbon Monoxide	A	A				A	A	A
Carbon Monoxide (Hot)								
Carbon Monoxide Gas- 1400F		B						
Carbon Monoxide Gas- 1600F		B						
Carbon Monoxide Gas- 900F		A						
Carbon Monoxide-Gas		A						
Carbon Tetrabromide								
Carbon Tetrachloride	X	B	X	A	C	C	X	X
Carbon Tetrachloride (dry)		B						
Carbon Tetrachloride (wet)	X	A						
Carbon Tetrachloride- 100%-70F	X	B						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Carbon Tetrachloride-5% to 10% Aqueous	C	B						
Carbon Tetrachloride-68F	X							
Carbon Tetrachloride- Aqueous Sol. 10%-70F	B	B						
Carbon Tetrachloride-CP (Dry)-70F		B						
Carbon Tetrachloride-CP (Dry)-Boiling		B						
Carbon Tetrachloride- Pure		A						
Carbon Tetrafluoride								
Carbonated Beverages		A						
Carbonated Water		A						
Carbonic Acid	A	B					A	A
Carbonic Acid Gas	A						A	A
Carbonic Acid-68F	A						A	A
Carbonic Acid-70F	A						A	A
Carbonic Acid-Sat'd.	A	A					A	A
Carbonic Anhydride								
Carbontetrachloride	X	B						
Casein (Casymer)								
Casing Head Gasoline								
Castor Oil	B	A		A	A	A	A	A
Castor Oil-68F	B						A	A
Catsup		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Caustic Lime		A						
Caustic Potash-10%-70F	A	A	C					
Caustic Potash-25%-70F	A	A	C					
Caustic Potash-50%	A	A	C					
Caustic Soda	A	A		A	A			
Caustic Soda Solution- 10%-70F	A		A					
Caustic Soda Solution- 25%-70F	A		B					
Caustic Soda Solution- 50%-70F	A		X					
Caustic Soda-Up to 40%	A	A	C					
Caustic-Baryta								
Caustic-Lime								
Caustic-Potash	A	A						
Cedarwood Oil, pure - Misc	C							
Cell Liquor	A	A		A	A			
Cellosize								
Cellosolve		A						
Cellosolve Acetate	A	C		A	C	X		
Cellosolve Butyl								
Cellube						X	X	X
Celluguard								
Cellulose Acetate		B						
Cellulose Acetate Butyrate	B							

<u>A=Great Application;</u> <u>B=Good Application (mild</u> <u>effect); C=Conditional Use</u> <u>(consult with ES</u> <u>Technical Staff); X=Do</u> <u>Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Cetylic Acid	B							
Chaulmoogric acid	X							
China Wood Oit (Tung Oil)	C							
Chinese Wood Oil								
Chinosol-Antis. Sol 1-500-70F		B						
Chickweed Killer	A							
Chloracetic Acid		X						
Chloramine-Dilute		C						
Chloranthraquinone	C							
Chlorascetic Acid-70F								
Chlorbenzol-Pure, Dry-70F		B						
Chlordane	C							
Chlorextol	C							
Chloric Acid		X						
Chloric Acid-10%		C						
Chloric Acid-20%		X						
Chloric Acid-70F		C						
Chlorinated Glue		A						
Chlorinated Solvents, Dry	C							
Chlorinated Solvents, Wet	C							
Chlorinated Water-10ppm		A						
Chlorinated Water-Saturated		B						
Chlorine (Dry)	A	A					C	C

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Chlorine (Plasma)	X							
Chlorine (Wet)	A	X					X	X
Chlorine (Wet/Dry)	A/A	A/X						
Chlorine Aqueous								
Chlorine Anhydrous Liquid		X						
Chlorine Dioxide						X	X	X
Chlorine Dioxide, 8% Cl as NaClO2 in solution	C							
Chlorine Gas (Dry)-0- 20PPM		A	X					
Chlorine Gas Dry			X	C	D			
Chlorine Gas Wet			X	C	D			
Chlorine Gas-20-50PPM		A						
Chlorine Gas-50+PPM		X						
Chlorine Gas-Dry		X	X					
Chlorine Gas-Dry Gas-70F			X					
Chlorine Gas-Moist		X	X					
Chlorine Gas-Moist Gas- 70F		C	X					
Chlorine Gas-Moist-212F		X	X					
Chlorine Trifluoride						X		
Chlorine Water		X						
Chlorine-100% (dry gas) -68F								
Chlorine-Liquid		X	X					
Chlorine, Dry	X							

A=Great Application: B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Chlorine, Wet	X		C					
Chloro 1 - Nitro Ethane (1- Chloro 1-Nitro Ethane)	C							
Chloro Acetic Acid	A	X						
Chloro Aceto Nitrile								
Chloro Acetone						X	B	B
Chloro Azotic Acid								
Chloro Benzal								
Chloro Benzene	X	A	X			X	X	X
Chloro Butadiene						X		
Chloro Butane (Chlorobutanol)				A	C			
Chloro Methane (Chloromethyl)								
Chloro Oxyfluorides	X							
Chloro Trifluoro Ethylene								
Chloro Xylenols	C							
Chloroacetic Acid	B	X						
Chloroacetic Acid-50%	B	X						
Chloroacetone	B							
Chloroacetyl Chloride	B							
Chloroacetyl Chloride								
Chloroamino Benzoic Acid	B							
Chloroaniline	B							
Chlorobenzaldehyde	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Chlorobenzene	X	A	X				X	X
Chlorobenzene (Mono)		A						
Chlorobenzene (Pure)- Concentrated		A	X					
Chlorobenzene-68F			X					
Chlorobenzene-70F			X					
Chlorobenzene-Dry		A	X					
Chlorobenzochloride	C							
Chlorobenzotrifluoride	C							
Chlorobenzyl Chloride		A						
Chlorobromomethane							X	X
Chlorobromopropane	C							
Chlorobutadiene								
Chlorobutane (Butyl Chloride)	B							
Chlorodane	B							
Chlorodifluoromethane, pure - Hydrocarbon, Aliphatic, Halogenated	X							
Chlorododecane							X	X
Chloroethane	B							
Chloroethane, Sulfonic Acid	B							
Chloroethylbenzene	C							
Chloroform	X	A	X	A	D	X	X	X

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Chloroform-100%-70F	X	A	X			X	X	X
Chloroform-68F	X	A	X			X	X	X
Chloroform-Dry	X	A	X			X	X	X
Chloroform-Dry-70F	X	A	X			X	X	X
Chlorohydrin	B							
Chloromethyl Benzene, pure - Hydrocarbon, Aromatic, Halogenated	C							
Chloronaphthalene or o- Chloronaphthalene	C					X	X	X
Chloronitrobenzene	C							
Chloropentane	B							
Chlorophenol or o- Chlorophenol	C							
Chloropicrin								
Chloroprene	C							
Chlorosilanes	X							
Chlorosulfonic Acid	B	X	X	C	C	X	X	X
Chlorosulfonic Acid-10%	B	X					C	C
Chlorosulfonic Acid-68F	B						X	X
Chlorosulphonic Acid, pure - Acid, Organic, Aromatic, Halogenated	C						X	X
Chlorotoluene	B					X	X	X
Chlorotoluene Sulfonic Acid	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Chlorotoluene, pure - Hydrocarbon, Aromatic, Halogenated	C							
Chlorotoluidine	C							
Chlorotrifluoroethylene (CTFE)	X							
Chlorox	B							
Chlorox (Bleach)	B	A	A					
Chloroxylols	X							
Chocolate Syrup		A						
Cholesterol	C							
Cholro Allyene								
Chrome Alum								
Chrome Alum-68F								
Chrome Ammonium Alum								
Chrome Plating Solutions	A					X	X	X
Chromic Acid	A/B	A	X			X	X	X
Chromic Acid (Cont. SO3) -50% Commercial	A/B	A	X					
Chromic Acid 10%	A/B	A	X	A	D			
Chromic Acid 30%	A/B	A	X					
Chromic Acid 5%	A/B	A	C					
Chromic Acid 50%	A/B	A	X	A	A			
Chromic Acid C.P.-10%- Boiling		A	X					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Chromic and Sulfuric Acid Mixture			X					
Chromic Chloride	X							
Chromic Fluorides	X							
Chromic Hydroxide	X							
Chromic Nitrates	X							
Chromic Oxide	C							
Chromic Oxide-88 WT% Aqueous Solution								
Chromic Phosphate	X							
Chromic Salts, Aq., Sat. -70F			A					
Chromic Sulfate	X							
Chromium Plating Bath-70F	A	B	C					
Chromium Plating, Barrel Chrome Bath 95F		X						
Chromium Plating, Black Chrome Bath 115		C						
Chromium Plating, Chromic-Sulfuric Bath		C						
Chromium Plating, Fluoride Bath 130F		X						
Chromium Plating, Fluosilicate Bath 95F		C						
Chromium Potassium Sulfate		C						
Chromium Salts	A		A					
Chromium Trioxide	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Coke Oven Gas	C	A						
Cole Oil								
Coolanol-Monsanto	X							
Cooking Oil						A		
Coolanol 20, 25R, 35R, 40 & 45 A (Monsanto)	C							
Copal Varnish		A						
Copper Acetate						B	B	B
Copper Acetate-Saturated		A						
Copper Acetate-Saturated-70F		B						
Copper Ammonium Acetate	B							
Copper Arsenate.Basic								
Copper Cabonate-Sat. Sol.		A						
Copper Carbonate-Sat. Sol. in 50% NH4OH		B						
Copper Carbonate-Sat'd		A						
Copper Chloride		X		A	A	A	A	A
Copper Chloride-1% Aerated-70F		B					A	A
Copper Chloride-1% Agitated & Aerated		A					A	A
Copper Chloride-5% Aerated		X					A	A
Copper Chloride-5% Aerated-70F							A	A
Copper Chloride-5% Agitated		B					A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Copper Chloride-68F							A	A
Copper Chloride- Anhydrous							A	A
Copper Chloride, Saturated		A					A	A
Copper Cyanide	A	A		A	A	A	A	A
Copper Cyanide-68F	A	A		A	A	A	A	A
Copper Cyanide- Saturated-Boiling		B					A	A
Copper Floborate		X						
Copper Fluoride-2%								
Copper Fluoride-68F								
Copper Fluoroborate		X						
Copper Gluconate	B							
Copper Nitrate		A		A	A			
Copper Nitrate-1% to 5%		A						
Copper Nitrate-5%-70F		B						
Copper Nitrate-50% Aqueous		A						
Copper Nitrate-50%- Boiling		B						
Copper Nitrate-68F								
Copper Nitrite								
Copper Nitrate-30%		A						
Copper Oxide	B							
Copper Plating (Acid), Copper Fluoborate		X						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Copper Plating (Acid), Copper Sulfate Bath		X						
Copper Plating (Cyanide), Copper Strike Bath		A						
Copper Plating (Cyanide), High Speed Bath		A						
Copper Plating (Cyanide), Rochelle Salt Bath		A						
Copper Salts	A		A					
Copper Salts-Aq., Sat.-70 F	A		A					
Copper Sulfate	A	B		A	A	A	A	A
Copper Sulfate (5% Solution)	A	A					A	A
Copper Sulfate >5%	A	B					A	A
Copper Sulfate 5%	A	B					A	A
Copper Sulfate-10%	A						A	A
Copper Sulfate-50%	A						A	A
Copper Sulfate, Saturated	A	A					A	A
Copper Sulfide	A							
Copper Sulphate	A							
Copper Sulphate-5%	A	A						
Copper Sulphate-5% Aerated-70F	A	B						
Copper Sulphate-68F	A							
Copper Sulphate-Saturated-Boiling	A	B						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Copper(Misc.), Copper (Electroless) 140 F								
Copper(Misc.), Copper Pyrophosphate 140		A						
Copperas Ferrous Sulfate								
Copra								
Corn Oil	A	A		A	D	A	B	B
Cottonseed Oil	A	A				A	B	B
Cottonseed Oil-70F	A	B				A	B	B
Cranberry Sauce								
Cream		A						
Cream of Tartar		A						
Creosol	X	A	X			C	C	C
Creosote	A	A				A	C	C
Creosote (Coal Tar)-Hot		B						
Creosote-68F	A	A						
Creosote, Wood	A	A						
Creosylic Acid				C	D			
Cresol	A	A	X					
Cresol (Cresol's)	A	A	X					
Cresol-90%	A	A	X					
Cresols	A	A	X					
Cresyl Hydrate								
Cresylic Acid	B	A				C	C	C

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Cresylic Acid-50%	B	A					C	C
Cresylic Acids-68F							C	C
Croton Aldehyde	A							
Crotonaldehyde-68F	A							
Crotonic Acid	C							
Crude Oil	C	A		A	A	A		
Crude Oil (Sour)	C	A		A	A			
Culture Media - Misc.	B							
Cumaldehyde	C							
Cumene	X	C		A	C		X	X
Cumene Hydroperoxide	X							
Cumyl Phenol-p								
Cupric Acetate								
Cupric Acid		B						
Cupric Arsenate								
Cupric Carbonate	A							
Cupric Chloride			A					
Cupric Chloride-105F		X	A					
Cupric Hydroxide	A							
Cupric Nitrate	A	A						
Cupric Sulfate	A							
Cutting Oil	C							
Cyanamide	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Cyanic Acid		A						
Cyanic Acid. Powdered								
Cyanides	A	A		A	A	A		
Cyanoacetic Acid								
Cyanogen Gas-70F		B						
Cyanomthane								
Cyanuric Chloride	X							
Cyaohydrin	X							
Cyclohexane	X	A	X	A	C	A	X	X
Cyclohexanone	B	A	X	A	C	X	X	X
Cyclohexnol	B	A	X			B	A	A
Cyclohexylamine	C							
Cyclohexylamine Carbonate	X							
Cyclohexylamine Laurate	C							
Cyclopentadiene	C							
Cyclopentanol	B							
Cyclopentanone	B							
Cyclopolyolefins	C							
Cyclohexyl Alcohol								
Cyclic Acid								
Cymene or p-Cymene	C							
D-Furaldehyde	B							
d-Limonene	X	A		A	A	X		

<u>A=Great Application;</u> <u>B=Good Application (mild</u> <u>effect); C=Conditional Use</u> <u>(consult with ES</u> <u>Technical Staff); X=Do</u> <u>Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
DDT in Kerosene	X	A						
Decahydronaphthalene	X		X					
Decahydroxnapthalene	X		X					
Decyl Alcohol	B							
Decyl Aldehyde	B							
Decyl Butyl Phthalate	C							
Decyl Carbinol	C							
Dental Gas								
Deoxycholate, pure - Detergent	X							
depc, pure - Misc.	B							
Detergent Solutions	A	A				A	A	A
Detergent-Water Solutions	A	A				A	A	A
Detergents	A	A	A			A	A	A
Detergents (Heavy Duty)	A	A	A			A	A	A
Detergents-High Conc.-70 F	A	A	A				A	A
Detergents-Normal Conc. -70F	A	A	A			A	A	A
Detergents, Synthetic-All Conc.-68F	A	A	A				A	A
Deuterium Oxide								
Developing Fluid & Solutions (Photo)							A	A
Developing Fluids	B	A				A	A	A
Developing Solutions	B	A				A	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Dextran Sulfate, pure - Misc., Sugar	A							
Dextran, pure - Misc., Sugar	A							
Dextrin		B						
Dextrin (Starch Gum)-Sat'd.		A						
Dextron								
Dextronic Acid								
Dextrose		A						
Di (2ethylhexyl) Adipate	B							
Di (2ethylhexyl) Phthalate	C							
DI Water	A							
Di- Tert-Butyl Peroxide	X							
Di-Ester Lubricant MIL-L-7808								
Di-ester Lubricant MIL-L-7808	C							
Di-Ester Lubricants-Synthetic								
Di-Ester Synthetic Lubricants	C							
Di-Iso-Butylene	X							
Di-Iso-Decyl Phthalate	B							
Di-Iso-Propanolamine	B							
Di-Iso-Propyl Ether	B							
Di-Iso-Propyl Ketone	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Diacetic Acid								
Diacetic Ester								
Diacetic Ether								
Diacetone	A	A						
Diacetone Alcohol	A	A				X	A	A
Diacetylmethane	B							
Diacetyl Acetic Acid								
Dialkyl Sulfates	B							
Diallyl Ether	X							
Diallyl Phthalate	B							
Diamine (Diamidogen)								
Diammonium Phosphate	A							
Diamyl Naphthalene	X							
Diamylamine	B							
Diamylene	C							
Diamylphenol	X							
Diazinon	B							
Diazo Salts - Misc., Salts	X							
Dibasic Potassium Phosphate, pure - Salt, Inorganic	B							
Dibasic Sodium Phosphate, pure - Salt, Inorganic	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Dibenzopyrrole, pure - Hydrocarbon, Aromatic, Heterocyclic	B							
Dibenzyl Ether						X	B	B
Dibenzyl Sebecate							X	X
Diborane	X							
Dibromo Benzene								
Dibromo Ethyl Benzene								
Dibromo Methane								
Dibromoethane	C							
Dibutoxyethyl Phthalate		A						
Dibutyl								
Dibutyl Acetate								
Dibutyl Amine						X	X	X
Dibutyl Cellosolve Adipate	B							
Dibutyl Ether	B					C	C	C
Dibutyl Methyleneidithio Glycolate	C							
Dibutyl Phthalate	B	A		A	A	X	X	X
Dibutyl Phthalate-68F	B					X	X	X
Dibutyl Sebecate	B					X	X	X
Dibutyl Thioglycolate	C							
Dibutyl Thiourea	C							
Dibutylamine	B							
Dicalcium Phosphate	A							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Dichlorethane	B	A						
Dichloro Acetic Acid				C	D			
Dichloro Butane								
Dichloro Difluoro Methane (Freon 12)								
Dichloro Ethane	X	B						
Dichloroethylene	C							
Dichloro-Isopropyl Ether						X	X	X
Dichloroaniline	B							
Dichlorobenzene	C	A		A	C	X	X	X
Dichlorobenzene -68F	C					X	X	X
Dichlorobenzene or o- Dichlorobenzene	C						X	X
Dichlorobenzene or p- Dichlorobenzene	C						X	X
Dichlorobenzene-p (Paradow)	C						X	X
Dichlorobutene	C							
Dichlorodifluoromethane- 68F								
Dichlorodiphenyl- Dichloroethane (DDD)	C							
Dichloroethane-Boiling		B						
Dichloroethylene		C						
Dichloroethylene-68F								
Dichlorohydrin	B							
Dichloroisopropyl Ether	C						X	X

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Diethyl Malonate, pure - Ester, Aliphatic	B							
Diethylacetamide, pure - Amine, Aliphatic	X							
Diethylamine	B	A		A	D			
Diethylamine, pure - Amine, Aliphatic	C							
Diethylaniline	B							
Diethylene Dioxide								
Diethylene Ether						X	C	C
Diethylene Glyco-Butyl Ether								
Diethylene Glycol	A	A				A	A	A
Diethylene Oxide	A							
Diethytriamine	A							
Diethylenetriamine	A							
Diethylpyrocarbonate, pure - Misc.	B							
Difluoro Dibromo Methane								
Difluoroethane	C							
Difluoromonochloroethane	C							
Dihydroxydiphenylsulfone	B							
Dihydroxy Diethyl Ether	A							
Dihydroxy Succinic Acid	A							
Dihydroxydiethyl Ether	A							

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Diisobutyl Ketone	C							
Diisobutylcarbinol	C							
Diisopropyl Benzene							X	X
Diisobutyl Ketone	C						X	X
Diisodecyl Phthalate	C							
Diisooctyl Adipate	C							
Diisooctyl Phthalate	C							
Dimethyl								
Dimethyl Acetamide	A							
Dimethyl Amine								
Dimethyl Aniline		B		A	C			
Dimethyl Aniline							X	X
Dimethyl Benzene								
Dimethyl Carbinol	A							
Dimethyl Disulfide (DMDS)	C							
Dimethyl Ether		B						
Dimethyl Ethyl Methane								
Dimethyl Formaldehyde	B							
Dimethyl Formamide	A	A	X	C		B	C	C
Dimethyl Hydrazine	B							
Dimethyl Ketone	B							
Dimethyl Phenyl Carbinol	C							
Dimethyl Phenyl Methanol	C							

<u>A=Great Application;</u> <u>B=Good Application (mild</u> <u>effect); C=Conditional Use</u> <u>(consult with ES</u> <u>Technical Staff); X=Do</u> <u>Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Dimethyl Phthalate	B					X	X	X
Dimethyl Sulfate	B							
Dimethyl Sulfide	B							
Dimethyl Sulfoxide (DMSO)	A							
Dimethyl-3-Pentanone	C							
Dimethyl-4-Heptanone	C							
Dimethylamine	A	A						
Dimethylaniline	B							
Dimethylbenzene	X							
Dimethylbutane	C							
Dimethylformamide	A							
Dimethylhydrazine								
Dinitro Benzene				A				
Dinitro Toluene						X	X	X
Dinitrochlorobenzene- Melted and Solidufied		B						
Dinitrogen Tetroxide	X							
Dinonyl Phthalate								
Diethyl Adipate	C							
Diethyl Amine								
Diethyl Phthalate	A						X	X
Diethyl Phthalate-68F								
Diethyl Sebecate						X	X	X
Diethylamine	C							

<u>A=Great Application;</u> <u>B=Good Application (mild</u> <u>effect); C=Conditional Use</u> <u>(consult with ES</u> <u>Technical Staff); X=Do</u> <u>Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Divinyl Benzene	X			A				
Divinyl Ether								
Divinyl Oxide								
Dixan Solution			A					
DMAC, pure - Amine, Aliphatic	B							
DMF, pure - Amine, Aliphatic	B							
DMSO, pure - Misc.	B							
Dow Corning - 11	B							
Dow Corning - 1265 Fluorosilicone Fluid	B							
Dow Corning -200	B							
Dow Corning -33	B							
Dow Corning -4	B							
Dow Corning -44	B							
Dow Corning -5	B							
Dow Corning -510	B							
Dow Corning -55	B							
Dow Corning -550	B							
Dow Corning 1208, 4050, 6620, F-60, xF-60	B							
Dow Corning 220	B							
Dowanol P Mix	B							
Dowtherm A		A					X	X

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Dowtherm E							X	X
Dowtherm Oil							X	X
Dowtherm SR-1							X	X
Dowtherm-209. 50% Solution							X	X
Drinking Water	A	A	A	A	A	A	A	A
Dry Cleaning Fluids	B	A				C	X	X
Dry Cleaning Solvent	B	A				C	X	X
Drycid								
DTE 20 Series	C							
DTE Light Oil								
DTE named series, Mobil, light-heavy	X							
Dyes		A						
Dyewood Liquor-70F		B						
Dyewood-Liquor		A						
Earth Pitch								
Earthnut Oil								
EDTA, pure- Misc., Chelator	B							
Elayl Chloride								
Elco 28-EP Lubricant								
Electrolytes	A	A						
Epoxy Resins	A	A						
Epsom Salt (Magnesium Sulphate)-Cold/Hot		B						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Epsom Salts		A						
Erucic Acid	B							
Essential Oils	B							
Ethanamide								
Ethane	D	A				A	B	B
Ethane Dioic Acid								
Ethane Nitrile								
Ethane Thiol								
Ethane-68F								
Ethanoic Acid (See Acetic Acid)	A							
Ethanoic Anhydride								
Ethanol	A	A						
Ethanolamine	A	A				B	B	B
Ether	B	A	X					
Ether-70F	B	B	X					
Ethers	B	A	X					
Ethoxy Ethanol				A	C			
Ethoxyethyl Acetate (EGMEEA)	B							
Ethyl		A						
Ethyl -3-Oxobutanoate								
Ethyl Acetoacetate	A					X	C	C
Ethyl Acetate	A	A	X	A	C	X	C	C

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ethyl Chloroformate								
Ethyl Cyanide								
Ethyl Cyanoacetate, pure - Ester, Aliphatic, Cyano	B							
Ethyl Dichloride				A	X			
Ethyl Digol, pure - Ether, Aiphatic, Polyol	B							
Ethyl Dimethyl Acetate								
Ethyl Ether	B	A				C	C	C
Ethyl Ether-68F	B	A				C	C	C
Ethyl Formate	A	A				X	B	B
Ethyl Formate-68F	A					X	B	B
Ethyl Formic Ester								
Ethyl Glycol	A	A						
Ethyl Hexanol	A							
Ethyl Iodide	B							
Ethyl Lactate-68F								
Ethyl Mercaptan		A				X		
Ethyl Nitrite	B							
Ethyl Oxalate	A					X	C	C
Ethyl Phthalate	B							
Ethyl Propyl Oxide								
Ethyl Pyridine	C							
Ethyl Silicate	A					A	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ethyl Sterate	C							
Ethyl Sulfate		D		A	A			
Ethyl Sulfohydrate								
Ethyl Sulphate-68F								
Ethyl Tertiary Butyl Ether	X							
Ethyl Valerate	C							
Ethyl-1-Butanol	B							
Ethyl-N-Butyl Ketone	B							
Ethylacrylic Acid	C							
Ethylamine	B							
Ethylcyclopentane	C							
Ethylene						A		
Ethylene Bromide		A						
Ethylene Bromide-Dry		A						
Ethylene Carboxylic Acid								
Ethylene Chlorhydrin	A	B				X	B	B
Ethylene Chlorhydrin-68F	A					X	B	B
Ethylene Chloride	A	A	X				B	B
Ethylene Chloride-100% -70F			X				B	B
Ethylene Chloride-68F			X				B	B
Ethylene Chloride-Dry		A					B	B
Ethylene Cyanohedrin	C							
Ethylene Diamine	A	B				A	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ethylene Dibromide-68F	C							
Ethylene Dichloride	A	A	X			X	X	X
Ethylene Dichloride-68F	A	A	X			X	X	X
Ethylene Dichloride-Dry	A	A	X					
Ethylene Glycol	A	A	A	A	A	A	A	A
Ethylene Glycol Monomethyl Ether	A							
Ethylene Glycol-68	A		A					
Ethylene Glycol-Conc.-70 F	A	B	A					
Ethylene Hydrochloride	C							
Ethylene Monoacetate								
Ethylene Nitrate, pure - Misc.	X							
Ethylene Oxide	A	A				X	X	X
Ethylene Trichloride						X	X	X
Ethyleneimine	X							
Ethylic Acid (See Acetic Acid)								
Ethylmorpholene Stannous Octotate (50/50 mix)	C							
Ethylmorpholine	C							
Ethylsulfuric Acid	B							
Ethyne								
EtO Gas, pure - Ether, Cyclic	C							
EtO Liquid, pure - Ether Cyclic	C							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
EtO, 100% - Ether, Cyclic	C							
EtO, pure - Ether, Cyclic	C							
Fargo - 2% aqueous	A							
Fat Lime								
Fatty Acids	B	A		A	A	B	B	B
FC-43 Heptacosofluorotri-butylamine	B							
Ferric Bromide	A							
Ferric Chloride	A	X		A	A	A	A	A
Ferric Chloride (Aqueous) -Sat'd	A	X					A	A
Ferric Chloride-1% Still	A	A					A	A
Ferric Chloride-1% Still-Boiling	A	X					A	A
Ferric Chloride-5% Aerated	A	X					A	A
Ferric Chloride-5% Agitated	A	X					A	A
Ferric Chloride-5% Still	A	X					A	A
Ferric Ferrocyanide	B						A	A
Ferric Hydroxide		A						
Ferric Hydroxide-70F		B						
Ferric Hydroxide-Sat'd		A						
Ferric Nitrate-1%-5%	A	A						
Ferric Nitrate	A	A		A	A	A	A	A
Ferric Nitrate-68F	A	A					A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ferric Nitrate-All Concentrations-70F	A	A					A	A
Ferric Nitrate-Sat'd	A	A					A	A
Ferric Salts	A	A						
Ferric Sulfate	A	A	A			A	A	A
Ferric Sulfate, Saturated	A	A	A			A	A	A
Ferric Sulphate	A	A	A			A	A	A
Ferric Sulphate -1% to 5%	A	A	A			A	A	A
Ferric Sulphate-10% & 50%-70F	A	A	A			A	A	A
Ferrous Ammonium Sulfate	B							
Ferrous Carbonate	B							
Ferrous Chloride	A			A	C			
Ferrous Chloride-68F	A							
Ferrous Chloride-Sat'd	A	X						
Ferrous Chloride-Saturated-70F	A							
Ferrous Chloride, Saturated	A							
Ferrous Hydroxide								
Ferrous Hydroxide-Sat'd		A						
Ferrous Iodide	B							
Ferrous Nitrate		A						
Ferrous Sulfate	A	A						
Ferrous Sulphate-10%-70 F	A	B						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Ferrous Sulphate-10%-Boiling	A	B						
Ferrous Sulphate-68F	A							
Ferrous Sulphate-Dilute	A	A						
Ferrous Tartrate	B							
Fertilizer						A		
Ficoll-Hypaque - Misc.	B							
Firewood Oil								
Fish Oil		A				A		
Fisher Reagent	C							
Fixing Salt			A					
Flourinated Cyclic Ethers								
Flue Gas		A						
Fluoborate Salts	A							
Fluorboric Acid	A	B		A	A	A	A	A
Fluorides - Salt, Inorganic	B							
Fluorinated Cyclic Ethers								
Fluorine	X	A						
Fluorine (Gas)-70F	X	A						
Fluorine (Liquid)	X	A						
Fluorine Gas (Dry)-100%	X	A						
Fluorine Gas (Wet)	X	A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Fluoroform (Trifluoromethane)	X							
Fluorolube						A	A	A
Fluorophosphoric Acid	X							
Fluorosulfonic Acid	X							
Fluosilicic								
Fluosilicic Acid	A	B				A	A	A
Fluosilicic Acid-50%	A	C				A	A	A
Foam, Fire	A	A		A	A			
Food Pastes		A						
Formaldehyde	A	A	C			B	A	A
Formaldehyde 40%	A	A	C			B	A	A
Formaldehyde-35%	A	A	C			B	A	A
Formaldehyde-37%	A	A	C			B	A	A
Formaldehyde-40% w/w in water-68F	A	A	C			B	A	A
Formaldehyde-50%	A	A	C			B	A	A
Formaldehyde-Dilute	A	A	B			B	A	A
Formaldehyde, 100%	A	A	C			B	A	A
Formaldehyde, 30%	A	A	C			B	A	A
Formaldehyde, 37%	A	A	C			B	A	A
Formaldehyde, 40%	A	A	C			B	A	A
Formalin	A		C				A	A
Formalin-Formaldehyde 40%-70F	A	B	C				A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Freon	X	A						
Freon - pure - Hydrocarbon, Aliphatic, Halogenated	B							
Freon 11	B	A				A	B	B
Freon 112						B		
Freon 113	X	A				A	A	A
Freon 114		A				A	A	A
Freon 114B2								
Freon 115						A	A	A
Freon 12		A				A	A	A
Freon 12 and ASTM Oil #2 (50/50 mixt)								
Freon 12 and Suniso 4G (50/50 mixt)								
Freon 124, (Chlorotetrafluoroethane	X							
Freon 21		A				X	B	B
Freon 218								
Freon 22	X	A				X	A	A
Freon TC							A	A
Freon TF	X	A						
Freon TMC								
Freon, 113 - High and Low Aniline Oil	X							
Freon, 123 (Dichlorotrifluoroethane	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Freon, 125 (Pentafluoroethane)	X							
Freon, 134a (Tetrafluoroethane)	B							
Freon, 141b (Dichlorofluoroethane)	X							
Fructose		A	A					
Fruit Juice		A						
Fruit Juices		A						
Fruit Juices-70F		B						
Fuel Oil	C/B	A		A	D	A	B	B
Fuel Oil (Containing H2SO4)-Hot	C	B						
Fuel Oil Acidic	B/C	A	X					
Fuel Oil-#6	B	A	X					
Fuel Oil-70F	B	A	X					
Fuel Oil-Hot	C	B	X					
Fuel Oils	C/B	A	X					
Fuel, Oil, 1, and 2	C	A	X					
Fuel, pure - Hydrocarbon, Mixture	B	A	X					
Fuels ASTM #1 Oil	A	A	X					
Fuels ASTM #2 Oil	A	A	X					
Fuels ASTM #3 Oil	B	A	X					
Fuels ASTM #4 Oil	C	A	X					
Fuels ASTM Ref Fuel A	B	A	X					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Fuels ASTM Ref Fuel B	B	A	X					
Fuels ASTM Ref Fuel C	C	A	X					
Fumaric Acid						A	B	B
Fumarole Acid								
Fuming Sulfuric Acid								
Fuming Sulphuric Acid (20/25% Oleum)	C							
Furniture Polish			X					
Furaldehyde								
Furaldehyde-2								
Furan (Furfuran)	C	A				X	X	X
Furan Resin	C	A					X	X
Furan, Furfuran	C	A				X	X	X
Furfural	B	A				X	B	B
Furfural-68F	B						B	B
Furfural-70F	B	B					B	B
Furfuran	B							
Furfuryl Alcohol	B			A	A			
Furoic Acid	X							
Furol								
Furyl Carbinol								
Fused Magnesium Chloride								
Fusel Oil								
Fyrquel 150 220 300 550	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Fyrquel 90, 100, 500	B							
Gallic Acid	B	A				B	B	B
Gallic Acid-5%-150F	B	B				B	B	B
Gallic Acid-5%-70F	B	B				B	B	B
Gallic Acid-5%-Room to Boiling	B	A				B	B	B
Gallic Acid-68F	B					B	B	B
Gallic Acid, Powder	B					B	B	B
Gallic Acid, Saturated	B					B	B	B
Gallic Acids-Saturated (212F)-Boiling	B	B				B	B	B
Gallontannic Acid								
Garlic Acid								
Gasohol		A				A		
Gasoline	B	A		A	A	A	B	B
Gasoline-100 Octane	B	A				A	B	B
Gasoline-40 Aromatic	B	A				A	B	B
Gasoline-65 Octane	B	A				A	B	B
Gasoline-70F	B	A				A	B	B
Gasoline-Aviation	B	A				A	B	B
Gasoline-Casing Head								
Gasoline-Ethyl								
Gasoline, Leaded	B	A				A		
Gasoline, Regular	B	A				A		

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Gasoline, Regular-70F	B	A				A		
Gasoline, Sour		A				A		
Gasoline, Super-70F	B	A				A	B	B
Gasoline, Unleaded	B	A				A	B	B
Gasoline, White								
Gaultheria Oil								
Gelatin		X				A	A	A
Gelatine-70F		B				A	A	A
German Saltpeter								
Germane (Germanium Tetrahydride)	X							
Glacial Acetic Acid-68F								
Glacial Acrylic Acid	A							
Glauber's Salt		A						
Glauber's Salt-Solution- Hot		A						
GIn-70F								
Gluconic Acid	B							
Glucose	A	A				A	A	A
Glue	A	A				A	A	A
Glue (Animal)								
Glue P.V.A		A						
Glue-Dry		A						
Glue-Dry-70F		B						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Glue-Solution Acid-70 and 140F		B						
Glue-Solution Acid-Hot		A						
Glutamic Acid	B							
Glutaraldehyde Disinfected - Aldehyde, Aliphatic, Solution	B							
Glutaraldehyde, pure - Aldehyde, Aliphatic	B							
Glycerin	A	A	B			A	A	A
Glycerin, Aq.-Low Conc. -70%	A	A	B			A	A	A
Glycerine	A	A	B	A	A	A	A	A
Glycerine-100%-70F	A	A	B			A	A	A
Glycerine-68F	A	A	B			A	A	A
Glycerine-70F	A	A	B			A	A	A
Glycerinum								
Glycerol	A							
Glycerol Dichlorohydrin	B							
Glycerol Monobenzyl Ether-68F								
Glycerol Monochlorohydrin	B							
Glycerol Triacete	B							
Glycerophosphoric Acid	B							
Glycidol	B							
Glycogenic Acid	B							
Glycol	A	A	B	A	A	A	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Glycol Acetate								
Glycol Alcohol								
Glycol Amine		A						
Glycol Monoether	X	A						
Glycol- 100%- 70F	A	A						
Glycol, Aq.- High Conc.- 70F	A	A						
Glycol, Aq.- Low Conc.- 70F	A	A						
Glycolic Acid- 68F								
Glycolic Acid- Sat'd.		A						
Glycols								
Glucose							A	A
Glycoxylic Acid	B							
Glyoxal		A						
Glue							A	A
Gold Monocyanide	X	A						
Gold Plating Cyanide 150F		A						
Gold Plating, Acid 75F		C						
Gold Plating, Neutral 75 F		C						
Grape Juice		A		A	A			
Grease		A						
Grease Light								
Green Copperas (Vitroil)	A							
Green Liquor (Sulfate)	A					B	B	B

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Green Liquour	A	A		A	A	B	B	B
Guanidine Hydrochloride, pure - Amine Salt	B							
Guanidine Isothicyanate, pure - Amine, Salt	B							
Guanidine Thiocyanate, pure - Amine, Salt	B							
Gulfcrown Grease	C							
Gypsum		A						
Gypsum- Slurry		A						
Haemo-Sol detergent - Detergent	B							
Halon		A						
Helium	A	A						
Hepar Calcis								
Hepatic Gas								
Heptachlorobutene	C							
Heptaldehyde (Heptanal)	B							
Heptanal	B							
Heptane	X	A	X	A	A			
Heptanoic Acid	A							
Heptane Carboxylic Acid	A							
Heptanone	B							
Hexachloroacetone	B							
Hexachlorobutadiene	C							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Histowax								
Home Orchard Spray	A							
Honey		A						
Houghto-Safe 1055 phosphate ester	B							
Houghto-Safe 416 & 500 Series	B							
Houghto-Safe 5040 (Water/Oil Emulsion)								
Houghto-Safe 620 Water/Glycol								
Household Bleach - Base/Caustic, Oxidizer	C							
Hydraulic Fluids (Pydrauls)	A		A				A	A
Hydraulic Oil	B	A	A				A	A
Hydraulic Oil (Petroleum)	B		A				A	A
Hydraulic Oils (Petroleum)	B	A	A				A	A
Hydraulic Oils (Synthetic)	C	A	A				A	A
Hydrazine	A	A	X			B	B	B
Hydrazine (Anhydrous)	B							
Hydrazine Dihydrochloride	B							
Hydrazine Hydrate	C							
Hydrazobenzene								
Hydriodic Acid	C							
Hydro Bromic Acid	A	C	X				A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Hydro-Drive MIH-10 (Petroleum Base)	C							
Hydro-Drive MIH-10 (Petroleum Base)								
Hydro-Drive MIH-50 (Petroleum Base)	C							
Hydro-Drive MIH-50 (Petroleum Base)								
Hydroabietyl Alcohol	X							
Hydrobromic Acid	A	C				X	A	A
Hydrobromic Acid 100%	A	X						
Hydrobromic Acid 40%	A							
Hydrobromic Acid- 100% aq. sol.- 68F	A							
Hydrobromic Acid- 20%	A	X		A	C			
Hydrobromic Acid- 50%	A	X						
Hydrobromic Acid- 50% aq. sol.- 68F	A							
Hydrobromic Acid- All Concentrations- 70F	A	C/X						
Hydrobromic Acid- Boiling		X						
Hydrobromic Acid-40%	A							
Hydrobromic Acid, 69% - Acid, Organic	B							
Hydrocarbons		A						
Hydrochloric Acid (100%)	A	X	B					
Hydrochloric Acid (20%)	A	X	A					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Hydrochloric Acid (25%)	A		A	A	A			
Hydrochloric Acid (36%)	A		B					
Hydrochloric Acid (37%)	A	C	B			B	B	B
Hydrochloric Acid (All Conc.)	A		B					
Hydrochloric Acid (Cold) 37%	A	C	B					
Hydrochloric Acid (Dry Gas)		A						
Hydrochloric Acid Fumes-Concentrated- 1		X						
Hydrochloric Acid- 10% Un aerated		X						
Hydrochloric Acid- 20% Un aerated		X						
Hydrochloric Acid- 35%	A	C						
Hydrochloric Acid- 37%	A	C						
Hydrochloric Acid- All-100F		X						
Hydrochloric Acid- All-122F		X						
Hydrochloric Acid- All-160F		X						
Hydrochloric Acid-5% Un aerated		X						
Hydrochloric Acid-50%								
Hydrochloric Acid, >6N - Acid, Inorganic	B							
Hydrochloric Acid, 1N - Acid, Inorganic	B							
Hydrochloric Acid, 3 Molar to 158 F	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Hydrochloric Acid, 30% - Acid, Inorganic	B							
Hydrochloric Acid, 5% - Acid, Inorganic	B							
Hydrochloric Acid, 6N - Acid, Inorganic	B							
Hydrochloric Acid, Concentrated to 158 F	C							
Hydrochloric Acid, pure - Acid, Inorganic	B							
Hydrochloric Acid 35%	A							
Hydrocyanic Acid	A	B				B	B	B
Hydrocyanic Acid (20%)	A	X				A	A	A
Hydrocyanic Acid (Gas 10%)	A	X					A	A
Hydrocyanic Acid- 10%	A	A					A	A
Hydrofluoric Acid (100%)	X	X				X	X	X
Hydrofluoric Acid (20%)	A	X					A	A
Hydrofluoric Acid (25%)	B			A	C		A	A
Hydrofluoric Acid (49%)	B			C	C		B	B
Hydrofluoric Acid (50%)	B	X					B	B
Hydrofluoric Acid (75%)	C	X					C	C
Hydrofluoric Acid Vapors- 212F	X	X						
Hydrofluoric Acid- 30%	B	X						
Hydrofluoric Acid- 4%aq. sol.- 68F	A							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff);</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Hydrogen Dioxide (10%)	A							
Hydrogen Fluoride Anhydrous		A						
Hydrogen Fluoride- Anhydrous- 68F								
Hydrogen Fluoride- Anhydrous								
Hydrogen Gas	A	A				A	A	A
Hydrogen Iodine	D							
Hydrogen Oxide								
Hydrogen Peroxide	A	B		C	D			
Hydrogen Peroxide (10%)	A	B						
Hydrogen Peroxide (100%)	B	A	A					
Hydrogen Peroxide (30%)	A	B	A					
Hydrogen Peroxide (50%)	A	A	A					
Hydrogen Peroxide (90%)	B		A					
Hydrogen Peroxide 90%	B		A			X		
Hydrogen Peroxide Boiling		A						
Hydrogen Phosphide- 68F								
Hydrogen Selenide	X							
Hydrogen Sulfide- Aqua	A	A	A					
Hydrogen Sulfide- Dry	A	A						
Hydrogen Sulfide- Wet	A	A	A			X	A	A
Hydrogen Sulfide-Gas				A	A			

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Hydrogen Sulfide-Wet.Hot						X	B	B
Hydrogen Sulfide, Solution	A	A	A					
Hydrogen Sulfide, Aqueous Solution	A	A	A					
Hydrogen Sulfite		A						
Hydrogen Sulphide- Dry		A						
Hydrogen Sulphide- Dry- 70F		B						
Hydrogen Sulphide- Wet- 70F		B						
Hydrogen-Gas	A	A					A	A
Hydrolube-Water/Ethylene Glycol	B							
Hydroxy Benzene	C							
Hydroxyisobutyronirile	A							
Hydroxytoluene	C							
Hydrooxycitronellal	X							
Hydroquinol	C							
Hydroquinone		A				C	A	A
Hydroquinone - Sat'd.		A				C	A	A
Hyponne								
Hyposulphite Soda (Hypo)		A						
I.P.A.								
Ice Spar(Stone)								
Iminodi-1-Propanol	B							
Iminodiethanol	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Indium Sulfamate Plating R.T		C						
Indole	X							
Industron FF44								
Industron FF48								
Industron FF53								
Industron FF80								
Ink		C	X					
Insecticide	A					A		
Insulin	B							
Iodic Acid	B							
Iodine	A	X						
Iodine (In Alcohol)	A	B						
Iodine and Solutions	A	X						
Iodine Crystals, - Element, Solid	B							
Iodine Pentafluoride	X					X	X	X
Iodine- 10%	A	X						
Iodine- sol. in potassium iodide- 68F	A							
Iodine-70F	A	C						
Iodoacetic Acid, pure - Acid, Organic, Halogenated	X							
Iodoform	B	B						
Iodoform- 70F	B	B						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
IPA, 100% - Alcohol, Aliphatic	B							
IPA, 30% - Alcohol, Aliphatic	B							
IPA, pure - Alcohol, Aliphatic	B							
Iron Phosphate		A						
Iron Plating, Ferrous Am. Sulfate Bath 150		C						
Iron Plating, Ferrous Chloride Bath 190F		X						
Iron Plating, Fluoborate Bath 145F		X						
Iron Plating, Sulfamate 140F		X						
Iron Plating, Sulfate-chloride Bath 160F		X						
Iron Plating, Ferrous Sulfate Bath 150F		C						
Iron Salts			A					
Iso-Butanol, 100% - Alcohol Aliphatic	B							
Iso-Butanol, pure - Alcohol, Aliphatic	B							
Iso-Butyl Alcohol, 100% - Alcohol, Aliphatic	B					B	A	A
Iso-Butyl Alcohol, pure - Alcohol, Aliphatic	B					B	A	A
Iso-Butylamine	B							
Iso-Butylbromide	C							

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Isoamyl Valerate	X							
Isoamyl-p-Phenol								
Isoboreol	X							
Isobutane		A						
Isobutanol								
Isobutanol, pure - Alcohol, Aliphatic	B							
Isobutyl		A						
Isobutyl Acetate								
Isobutyl Alcohol		A				B	A	A
Isobutyl Alcohol, pure - Alcohol, Aliphatic	B					B	A	A
Isobutylcarbinol	B							
Isobutyl Methyl Ketone	X							
Isobutyl n-Butyrate								
Isobutyl Phosphate	B							
Isobutylene								
Isobutyraidehyde	C							
Isobutyric Acid								
Isocrotyl Chloride	X							
Isodecanol	C							
Isododecane								
Isoeugenol	C							
Isooctane	X	A	A			A	B	B

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Isocyanates	B							
Isopropyl		A						
Isopropyl Acetate		B		A	C	X	X	X
Isopropyl Alcohol	A	A	X	A	C	B	A	A
Isopropyl Alcohol- 68F	A		X				A	A
Isopropyl Alcohol-100%- 70F	A		X				A	A
Isopropyl Alcohols	A	A	X				A	A
Isopropyl Chloride						X		
Isopropyl Ether	B	A				B	B	B
Isopropyl Myristate, pure - Ester, Aliphatic	X							
Isopropylacetone	B							
Isopropylacetone, pure - Ketone, Aliphatic	X							
Isopropylamine	B							
Isotane								
Ispropyl Ether							B	B
Japanese Gelatin								
Japanese Islinglass								
Jet Fuel	A	A		A	C	A		
Jet Fuel (JP3,JP4,JP5)	A	A		A	C	A		
Jet Fuels: JP-1.A & A1	A	A		A	C	A		
Jet Fuels: JP-3	A	A		A	C	A		
Jet Fuels: JP-4	A	A		A	C	A		

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Kurrol's Salt								
Lacquer Thinners	X	A				X	X	X
Lacquers	X	A				X	X	X
Lactams-Amino Acids								
Lactic Acid	A	B	C	C	C	A	A	A
Lactic Acid (Hot)	A					A	A	A
Lactic Acid Cold	A					A	A	A
Lactic Acid Salts		A						
Lactic Acid- 1,5, and 10%- 70F	A	B	A				A	A
Lactic Acid- 1%- Boiling	A	B	A				A	A
Lactic Acid- 10%- 150 F to Boiling	A	B	A				A	A
Lactic Acid- 10%- Boiling	A	B	A				A	A
Lactic Acid- 25%	A	A	B				A	A
Lactic Acid- 5%	A	A	A				A	A
Lactic Acid- 5% Boiling	A	B	A				A	A
Lactic Acid- 5%- 150F	A	A	A				A	A
Lactic Acid- 80%	A	A	C				A	A
Lactones (Cyclic Esters)	C							
Lanotin- 70F								
Laquer	X							
Laquer Solvents	X	A						
Lard	A	A	C	A	A	A	C	C

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Lard (Animal Fat)	A	A	C	A	A		C	C
Lard Oil	A	A	C	A	A		C	C
Lard- 70F	A	A	C	A	A		C	C
Lard- Molten		A	X					
Lasso	A							
Latex		A						
Lauric Acid		A						
Lauryl Alcohol								
Lauryl Chloride		A		A	A			
Lavender Oil	B					B	C	C
LB 135	B							
Lead		A						
Lead (Molten)	X							
Lead Acetate		A	A	A	A	B	B	B
Lead Acetate- 5%- Boiling		B	A				B	B
Lead Acetate- 68F			A				B	B
Lead Acetate- Sat'd.		A	A				B	B
Lead Arsenate								
Lead Azide	X							
Lead Bromide	B							
Lead Carbonate	B							
Lead Chloride								
Lead Chromate	B							

<u>A=Great Application;</u> <u>B=Good Application (mild</u> <u>effect); C=Conditional Use</u> <u>(consult with ES</u> <u>Technical Staff); X=Do</u> <u>Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Lead Dioxide	B							
Lead Fluoborate Plating		C						
Lead Linoleate	B							
Lead Naphthenate	X							
Lead Nitrate	A	A				A	A	A
Lead Nitrate- 68F	A	A				A	A	A
Lead Nitrate- Sat'd.	A	A				A	A	A
Lead Oxide	B							
Lead Salts	A							
Lead Sulfamate		A				B	A	A
Lead Sulfate	A							
Lead Sulfate		C						
Lemon Oil		A						
Ligrion		A						
Lime	A	A						
Lime Bleach	A					A	B	B
Lime Saltpeter								
Lime Slurry		A						
Lime Soda								
Lime Sulfur	A	A				X	A	A
Limonene	X							
Lindol							C	C
Linoleic Acid	C	C				B	X	X

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Linseed Oil	B	A	C			A	B	B
Linseed Oil- 68F	B	A	C				B	B
Linseed Oil- 70F	B	A	C				B	B
Liquid Petroleum Gas (LPG)	X					A	B	B
Liquor.Sulfitic								
Lithium Broide				A	A			
Lithium Bromide								
Lithium Bromide (Saturated)								
Lithium Carbonate	B							
Lithium Chloride		A						
Lithium Citrate	B							
Lithium Grease	A							
Lithium Hydroxide		A		A	A			
Lithium Hypochlorite	B							
Lithium Nitrate	B							
Lithium Nitrite	B							
Lithium Perchlorate	B							
Lithium Salicylate	B							
Lithopone	B							
Lubricants	B	A						
Lubricating Oil (ASTM#1)	B	A				A	B	B
Lubricating Oil (ASTM#2)	B	A				A	B	B
Lubricating Oil (ASTM#3)	B	A				A	B	B

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Lubricating Oils (Crude & Refined)	B	A				A	B	B
Lubricating Oils (Petroleum)	B	A				A	B	B
Lubricating Oils (Synthetic base)	B	A				A	B	B
Ludox		A						
Lumarith E.C.								
Lye	B	A				B	B	B
Lye (Caustic)- 34%-230F	B	A						
Lye Solutions	A							
Lye: Ca(OH)2 Calcium Hydroxide	A	B						
Lye: KOH Potassium Hydroxide	A	A						
Lye: NaOH Sodium Hydroxide	A	B						
Lysine-Monohydrochloride-dl (Powder)								
Lysine-Dihydrochloride-dl (Powder)								
Lysol- 212F		A	C/X					
Lysol- 70F		B	C					
Magnesium Acetate	A							
Magnesium Ammonium Sulfate								
Magnesium Bisulfate		A						
Magnesium Bisulfite				A	A			

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Magnesium Bromide								
Magnesium Carbonate		A		A	A			
Magnesium Carbonate-68F		A						
Magnesium Carbonate-All Concentrations		B						
Magnesium Carbonate, Saturated								
Magnesium Chloride	A	B		A	A	A	A	A
Magnesium Chloride Sulfate	A						A	A
Magnesium Chloride- 1% to 5% Still	A	A						
Magnesium Chloride- 1% to 5% Still-Hot	A	B						
Magnesium Chloride- 1% -5%- Hot	A	B						
Magnesium Chloride- 1% -5%-70F	A	B						
Magnesium Chloride- 68F	A							
Magnesium Chloride- Sat'd.	A	X						
Magnesium Citrate								
Magnesium Fluoride		C						
Magnesium Hydrate	A							
Magnesium Hydroxide	A	A		A	A	B	A	A
Magnesium Hydroxide-68F	A	A				B	A	A
Magnesium Hydroxide-70F	A	A				B	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Malathion								
Maleic Acid	A	A				A	B	B
Maleic Acid- Sat'd.	A	A				A	B	B
Maleic Acid, 10%	A	A				A	B	B
Maleic Acid, 25%	A	A				A	B	B
Maleic Anhydride	A	A						
Maleic Hydrazide	B							
Maleinic Acid-25%	A	A						
Maleic Acid	A	A				A	B	B
Maleic Acid- 68F	A	A				A	B	B
Maleic Acid- Cold & Hot	A	A				A	B	B
Maleic Acid- Cold and Hot	A	A				A	B	B
Malonyl Nitrile								
Malt Salt								
Mandelic Acid	B							
Manganese Acetate	B							
Manganese Carbonate		A						
Manganese Chloride- 10% to 50% Aqueous		A						
Manganese Dioxide	B							
Manganese Gluconate	B							
Manganese Hypophosphite	B							
Manganese Linoleate	B							
Manganese Naphthenate	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Manganese Phosphate	B							
Manganese Salts	A							
Manganese Sulfate		A						
Manganous Chloride	B							
Manganous Phosphate	B							
Manganous Sulfate	A							
Malathion	A							
Mannitol	B							
Mash		A						
Mash- Hot		A						
Mayonnaise		A						
Mayonnaise- 70F		B						
Mayonnaise- Cold & Hot		A						
Meats (Unsalted)		A						
Mechanical Oil - Hydrocarbon, Mixture	C							
Meitylene, pure - Hydrocarbon, Aromatic	C							
Melamine		X						
Mercaptan	X							
Mercapto Acetic Acid (95%)								
Mercaptobenzothiazole (MBT)	X							
Mercuric Acetate	B							
Mercuric Bichloride- 0.07%		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Mercuric Chloride		X		A	C	A	A	A
Mercuric Chloride (Dilute Solution)		X					A	A
Mercuric Chloride- Dilute		X					A	A
Mercuric Cyanide		A						
Mercuric Cyanide- Sat'd.		A						
Mercuric Iodide	B							
Mercuric Nitrate	B							
Mercuric Salts			A					
Mercuric Sulfate	B							
Mercuric Sulfate- Sat'd.								
Mercuric Sulfite	B							
Mercurous Nitrate		A						
Mercurous Nitrate- Sat'd.		A						
Mercury	A	B	A			A	A	A
Mercury Chloride- Dil. Sol. - 70F		C					A	A
Mercury Fulminate	B							
Mercury Salts	A							
Mercury Vapours	A							
Mesityl Oxide	C					X	X	X
Meta-Nitroaniline	B							
Meta-Toluidine	X							
Metaldehyde	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Methacrylic Acid		A						
Methallyl Alcohol								
Methallyl Chloride	B							
Methanal								
Methanal-40%								
Methanamide								
Methane	X	A				A	B	B
Methane Carboxylic Acid	A							
Methanoic Acid	A							
Methanol	A	A		A	C	A		
Methanol- 70F	A	A		A	C	A		
Methenyl Iodide								
Methionine-dl (Powder)								
Methoxy Ethanol	A							
Methoxy Methane								
Methoxychlor	X							
Methoxyethyl Oleate								
Methyl		A						
Methyl Abietate	X							
Methyl Acetal								
Methyl Acetate	A	A				X	B	B
Methyl Acetate (82%)	A						B	B
Methyl Acetoacetate	A							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Methyl Butyrate Chloride	B							
Methyl Carbitol								
Methyl Carbonate								
Methyl Cellosolve	A	A					B	B
Methyl Cellosolve Acetate, pure - Ether, Aliphatic, Polyol	C						B	B
Methyl Cellulose	A							
Methyl Chloride	B	A				X	X	X
Methyl Chloride- 68F						X	X	X
Methyl Chloride- Dry		A				X	X	X
Methyl Chloroacetate	B							
Methyl Chloroform		A						
Methyl Chloroformate								
Methyl Chlorosilanes	X							
Methyl Cyanide	A							
Methyl Ethyl Ketone	A	A	X	A	A	X	X	X
Methyl Ethyl Oleate	X						X	X
Methyl Formate		A				X	B	B
Methyl Hexanol	B							
Methyl Isobutyl Ketone	A	A					X	X
Methyl Isobutyl Ketone- 68F						X	X	X
Methyl Isocyanate	B							
Methyl Isopropyl Ketone		A						
Methyl Isovalerate	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Methyl Lactate	B							
Methyl Mercaptan	B							
Methyl Methacrylate	A/B					X	X	X
Methyl Pentadiene	X							
Methyl Phenol								
Methyl Phenylacetate	X							
Methyl Propyl Ether	B							
Methyl Salicylate	B						X	X
Methyl Styrene	X							
Methyl Sulfide	B							
Methyl Tertiary Butyl Ether (MTBE)	C							
Methyl Valerate	X							
Methyl-2-Butanol	B							
Methyl-2-Butanone	B							
Methyl-1-Butyl Ether, pure - Ether, Aliphatic	C							
Methyl-2-Hexanone	C							
Methyl-2-Pyrrolidone or n- Methyl-2-Pyrrolidone	B	A		A	B			
Methyl 1-2, 4-Pentanediol	A							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Methylene Oxide								
Methylene Salicylas								
Methylglycerol	B							
Methylisobutyl Carbinol	B							
Methylisobutyl Ketone	B							
Methylisopropyl Ketone	B							
Methylacetonitrile	A							
Methylphenol	B							
Methylpyrrolidone	B	A						
Methylpropyl Carbinol	A							
Methylpropyl Ketone	B							
Methylsulfuric Acid								
Metrizamide - Misc.	B							
Meyhylene Chloride		A						
MIL-F-81912 (JP-9)	C	A				A	A	A
MIL-F-82522 (RJ-4)	C	A				A	A	A
MIL-H-46170 -15° F to +400° F	X	A				A	A	A
MIL-H-46170 -20° F to +275° F	X	A				X	X	X
MIL-H-46170 -55° F to +275° F	C	A				X	X	X
MIL-H-46170 -65° F to +275° F	C	A				A	A	A
MIL-H-5559A	C	A				A	A	A
MIL-H-5606 -65° F to +235° F	C	A				A	A	A
MIL-H-5606 -65° F to 235° F	C	A				A	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff);</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
MIL-T-83133	C	A				A	A	A
MIL-T-9188B	C	A				A	A	A
Milk	A	A		A	A	A	A	A
Milk (Fresh or Sour)- Cold or Hot	A	B		A	A	A	A	A
Milk (Whole)	A	A		A	A	A	A	A
Milk Acid-50%	A	A						
Milk of Magnesia								
Milk- 70F	A	A				A	A	A
Mine Water- Acid	A	A				A	A	A
Mineral Naptha								
Mineral Oil	A	A	C			A	B	B
Mineral Spirits	B/C	A		A	A	A		
Mixed Acids- 15% H2SO4 + 5%HNO3 + 80%		B						
Mixed Acids- 15% H2SO4 + 5%HNO3 + 80%		B						
Mixed Acids- 50% H2SO4 + 50%HNO3- 200		B						
Mixed Acids- 50% H2SO4 + 50%HNO3- Boil								
Mixed Acids- 50% H2SO4 + 50%HNO3- Col		B						
Mixed Acids- 70% H2SO4 + 10%HNO3 + 20		B						
Mixed Acids- 70% H2SO4 + 10%HNO3 + 20		C						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Mixed Acids- 70% H2SO4 + 10%HNO3 + 20		B						
MLO-7277 Hydr.								
MLO-7557								
MLO-8200 Hyr.								
MLO-8515								
Mobasic Sodium Phosphate, pure - Salt, Inorganic	B							
Mobil 24 DTE								
Mobil 254 Lubricant	X							
Mobil Delvac 1100,1110,1120,1130								
Mobil SHC 500 Series	C							
Mobil SHC 600 Series	C							
Mobilgas WA200 ATF	C							
Mobilgear 600 Series	C							
Mobilgear SHC ISO Series	C							
Mobilgrease HP	C							
Mobilgrease HTS	C							
Mobilgrease SM	C							
Mobilith AW Series	C							
Mobilith SHC Series	C							
Mobiljet II Lubricant	X							
Mobilmistlube Series	C							
Mobiloil SAE 20	C							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Molasses	A	B						
Molten Sulfur	B							
Molybdenum Disulfide Grease	C							
Molybdenum Oxide	B							
Molybdenum Trioxide	B							
Molybdic Acid	B							
Molybodic Acid- 5%- 70F		B						
Molybolic acid- 5%		A						
Monoammonium Phosphate								
Monobasic Potassium Phosphate, pure - Salt, Inorganic	B							
Monobromo Trifluoro Methane								
Monobromotoluene	X							
Monobutyl Paracresol	X							
Monochloracetone								
Monochlorethane								
Monochloro Phenol								
Monochloro Acetic Acid	A							
Monochloro Benzene	X						X	X
Monochloro Trifluoro Methane								
Monochloroacetic Acid	A							

<u>A=Great Application;</u> <u>B=Good Application (mild</u> <u>effect); C=Conditional Use</u> <u>(consult with ES</u> <u>Technical Staff); X=Do</u> <u>Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Monochloroacetic Acid- 50%	A	X						
Monochlorobenzene- 68F	X					X	X	X
Monochlorobenzene- Tech. - Pure	X	A				X	X	X
Monochlorobutene	X							
Monochlorohydrin	X							
Monoethanol Amine							X	X
Monoethanolamine		A					X	X
Monochlorodifluoromethar	B							
Monoethanol Amine	A							
Mononitrotoluene	B							
Monoethyl Amine	A							
Monoethylamine	A							
Mononitrotoluene & Dinitrotoluene (40/60 Mix)	B							
Morpholine	A	A						
Morrhua Oil								
Mosaic Gold								
Motor Oil	B	A	C			A		
Motor Oil- 70F	B	A	C			A		
Motor Spirits								
MTBE, pure - Ether, Aliphatic	B							
Mud, Drilling	A	A		A	A			

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Muriate of Ammonia								
Muriatic Acid	A	X		A	A			
Muriatic Acid- 70F	A	C						
Mustard		A					A	A
Mustard- 70F		B					A	A
Myristic Acid	X							
n Heptane								
n- Amyl Chloride		A						
n- Butyl Chloride		C						
n- Hexane		A						
N-Methylpyrrolidone (NMP)	B	A						
n- Octane		A						
n- Pentane	X	X				A		
n- Propyl Bromide		A						
n- Propyl Nitrate		A						
n-Butanol, pure - Alcohol, Aliphatic	B							
n-Butyl Acetate	A	C						
n-Butyl Acetate, pure - Ester, Aliphatic	C							
n-Butyl Alcohol, pure - Alcohol, Aliphatic	B							
n-Butyl Phthalate, pure - Ester, Aromatic	C							
n-Decane, pure - Hydrocarbon, Aliphatic	C					B	X	X

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Naphthalene- 68 F								
Naphthalonic Acid	X							
Naphthene								
Naphthylamine	X							
Naptha		A						
Naptha Crude- 70F		B						
Naptha Pure- 70F		B						
Napthalene	C	B						
Napthenic Acid								
Natural Gas	A	A				A	A	A
NAVSolve	A					A		
Neon Gas	A							
Neville Acid						C	C	C
Nickel Acetate	A					B	B	B
Nickel Ammonium Sulfate		A						
Nickel Ammonium Sulphate								
Nickel Chloride	A	B				A	A	A
Nickel Chloride Sol.- 70F	A	B				A	A	A
Nickel Chloride- 68F	A	B				A	A	A
Nickel Chloride- Sat'd.	A	B				A	A	A
Nickel Cyanide	B							
Nickel Nitrate	A	A						
Nickel Nitrate- 10%	A	A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Nickel Nitrate- 68F	A	A						
Nickel Nitrate- Sat'd.	A	A						
Nickel Plating, Electroless 200F								
Nickel Plating, Fluoborate 100-170F		C						
Nickel Plating, High Chloride 130-160F		C						
Nickel Plating, Sulfamate 100-140F		C						
Nickel Plating, Watts Type 115-160F		C						
Nickel Salts	A		A					
Nickel Sulfate	A	B				A	A	A
Nickel Sulfate- Sat'd.	A						A	A
Nickel Sulphate Sol.- 70F	A	B					A	A
Nickel Sulphate- 10%	A	A					A	A
Nicotinamide (Niacinamide)	X							
Nicotinamide Hydrochloride	B							
Nicotine		A						
Nicotine Bentonite								
Nicotine Sulfate								
Nicotinic Acid		C						
Nietylene								
Niroacellulose	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Nirodiphenyl	X							
Niter Cake						A	A	A
Niter cake- Fused		B					A	A
Nitrating Acid (<1% Acid)		A						
Nitrating Acid (<15% H2SO4)		C						
Nitrating Acid (<15% HNO3)		X						
Nitrating Acid (>15% H2SO4)		C						
Nitric Acid (5 to10%)	A	A				X	A	A
Nitric Acid- 10%	A	A		A	C	X	A	A
Nitric Acid- 10%aq. sol.- 68F	A	A				X	A	A
Nitric Acid- 100%	B	A	X			X	C	C
Nitric Acid- 20%	B	A	C			X	A	A
Nitric Acid- 25%	B	A	C	A	C	X	A	A
Nitric Acid- 25%aq. sol.- 68F	B	A	C			X	A	A
Nitric Acid- 30%	B	A	C			X	A	A
Nitric Acid- 35%	B	A	C			X	A	A
Nitric Acid- 40%	B	A	X			X	B	B
Nitric Acid- 5%	A	A	C			X	A	A
Nitric Acid- 5%- Boiling	A	A	C			X		
Nitric Acid- 5%aq. sol.- 68F	A	A	C			X	A	A
Nitric Acid- 50%	B	A	X	C	X	X	B	B
Nitric Acid- 50%	B	A	X			X	B	B
Nitric Acid- 50%- 70F	B	A	X			X	B	B

<u>A=Great Application;</u> <u>B=Good Application (mild</u> <u>effect); C=Conditional Use</u> <u>(consult with ES</u> <u>Technical Staff); X=Do</u> <u>Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Nitro Xanthic Acid								
Nitroaniline	B							
Nitrobenzene	X	B				X	X	X
Nitrobenzoic Acid	B							
Nitrochlorobenzene	B							
Nitrochloroform	B							
Nitrodiethylaniline	B							
Nitroethane	A					X		
Nitroethane- Tech.- Pure								
Nitrogen	A	A		A	A	A	A	A
Nitrogen Fertilizer Solution	A							
Nitrogen Gas		A						
Nitrogen Monoxide								
Nitrogen Oxides	A					X	X	X
Nitrogen Trifluoride	X							
Nitroglycerine	B							
Nitroglycerine		A						
Nitroglycerol	B							
Nitroglycol								
Nitroisopropylbenzene	B							
Nitromethane	A	A						
Nitromethane- Tech.- Pure	A	A						
Nitrophenol	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Nitropropane	C							
Nitrosulfuric Acid	X							
Nitrosyl Chloride								
Nitrothiophene	B							
Nitrotoluene	B							
Nitrous Acid	A	B						
Nitrous Acid- 10%		C						
Nitrous Acid- 5%		A						
Nitrous Acid- 5%- 70F		B						
Nitrous Oxide		A						
Nonane	C							
Nonanoic Acid	B							
Nonanol	B							
Noryl GE Phenolic	B							
Nycodenz - Misc.	B							
Nyvac FR200 Mobil	B							
Octadecane	C					A	B	B
Octanoic Acid	B							
Octanol	B							
Octyl		A						
Octyl Acetate	B							
Octyl Alcohol	B					B	A	A
Octyl Aldehyde	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Octyl Amine	B							
Octyl Carbinol	B							
Octyl Chloride	C							
Octyl Phthalate	X							
Octylene Glycol	B							
Oil of Vitriol								
Oil of Wintergreen, pure - Ester, Aromatic	C							
Oil, Mineral	A							
Oil, Paraffin, pure - Hydrocarbon, Mixture	C							
Oil, Sesame, pure - Misc.	X							
Oil, Vegetable	A			A	A			
Oil, Wintergreen, pure - Ester, Aromatic	X							
Oils- Mineral- Vegetable- Hot & Cold		A						
Oils-Crude- Hot & Cold	C	A		A	A	A		
Oils, Aniline		A						
Oils, Animal	A							
Oils, Anise		A						
Oils, Bay		A						
Oils, Bone		A						
Oils, Castor	B	A						
Oils, Cinnamon		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Oils, Citric		A						
Oils, Clove		A						
Oils, Coconut		A						
Oils, Cod Liver		A						
Oils, Corn		A						
Oils, Cotton Seed		A						
Oils, Cresote		A						
Oils, Crude- Cold and Hot		B						
Oils, Diesel Fuel (2D, 3D, 4D, 5D)		A						
Oils, Fuel (1, 2, 3, 5A, 5B, 6)		A						
Oils, Ginger		A						
Oils, Hydraulic (See Hydraulic)								
Oils, Lemon		A						
Oils, Linseed		A						
Oils, Mineral		A						
Oils, Olive		A						
Oils, Orange		A						
Oils, Palm		A						
Oils, Peanut		A						
Oils, Peppermint		A						
Oils, Pine		A						
Oils, Rape Seed		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Oils, Rosin		A						
Oils, Sesame Seed		A						
Oils, Silicone		A						
Oils, Soybean	C	A						
Oils, Sperm		A						
Oils, Tanning		A						
Oils, Transformer		A						
Oils, Turbine		A						
Oils, Veg. & Min.- Cold and Hot		B						
Olefins	X							
Oleic Acid	B	A	C			C	C	C
Oleic Acid- 300F	X	B	X			C		
Oleic Acid- 400F	X	B	X			X		
Oleic Acid- 68F	B	A	C			C		
Oleic Acid- 70F	B	A	C			C		
Oleum	X	A	X			B	C	C
Oleum (100%)	X	A	X			B		
Oleum (25%)	X	A	X			B		
Oleum Theobromatics								
Oleyl Alcohol	X							
Olive Oil	B	A				A	B	B
Orth-Dichlorobenzene	B						X	X
Ortho-Dichlorobenzol	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Oxygen-Liquid								
Oxygen, gas, pure - Element, Gas	C							
Ozonated Deionized Water	A	A		A		X		
Ozone	A	A		A		X	B	B
p-Tertiary Butyl Carechol								
p-Toluenesulfonic Acid (PTSA)	A	C		A	A	X		
Palm Oil		A						
Palm Oil- 70F								
Palmic Acid								
Palmitic Acid	A	A				A	B	B
Palmitic Acid (Powder)	A	A				A	B	B
Palmitic Acid- 10%	A	A				A	B	B
Palmitic Acid- 68F	A	A				A	B	B
Palmitic Acid- 70%	A	A				A	B	B
Para-Dichlorobenzene	C							
Para-Nitroaniline	B							
Para-Nitrobenzoic Acid	B							
Para-Nitrophenol	B							
Para-Toluene Sulfnic Acid	B							
Parachloride								
Paracymene	C							
Paraffin	B	A	C					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Paraffin- Cold and Hot	B	B	C					
Paraffin- Molten		A						
Parathlon	X							
Paregoric Compound		A						
Peanut Oil		A				A	B	B
Pectin (Liquor)	C		A					
Penicillin (Liquid)	C							
Penta Hydroxy Hexoic Acid								
Penta Methylene Amine								
Pentachlorophenol	B	A						
Pentachlorophenol, Dowicide "G" Sodium	B	A						
Pentafluoroethane (F-125)	X							
Pentane	X	C						
Pentyl Acetate	B							
Pentyl Alcohol	B							
Pentyl Bromide	C							
Pentyl Chloride	C							
Pentyl Ether	B							
Pentyl Pentanoate	C							
Pentylamine	A							
Peracetic Acid- 70%	B	C						
Perchlorethylene	X	A				C		
Perchloric Acid	A	C		C	X		A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Perchloric Acid- 10%	A	A					A	A
Perchloric Acid- 68F	A	C					A	A
Perchloric Acid, 25% - Acid, Inorganic, Oxidizer	A							
Perchloric Acid, 60% - Acid, Inorganic, Oxidizer	C							
Perchloric Acid, 70% - Acid, Inorganic, Oxidizer	C							
Perchloro Methane	X							
Perchloroethylene	B	A					X	X
Percoll - Misc.	B							
Perfluoropropane	X							
Perfluorotriethylamine	X							
Perhydrol								
Periciase								
Permachlor								
Permanganic Acid	X							
Persulfuric Acid (Caro's Acid)	X							
Peru Saltpeter								
Petrol								
Petrolatum		A						
Petrolatum Ether	C							
Petrolene								
Petroleum	C	A				A	B	B

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Petroleum - Above 250	X	A				C	X	X
Petroleum - Below 250	C	A				A	B	B
Petroleum Benzin								
Petroleum Ether	X	B						
Phenol	B	A					C	C
Phenol (10%)	A	A						
Phenol (Carbolic Acid)		A						
Phenol 70% 30% H2O								
Phenol 85%				C	C			
Phenol- CP- 70F		B						
Phenol- CP- Hot		B						
Phenol, 5%								
Phenol, 50% - Alcohol, Aromatic	C							
Phenol, 92% - Alcohol, Aromatic	C							
Phenol, Aq. Sat.- 70F								
Phenol, Crystals								
Phenol, Crystals, pure - Alcohol, Aromatic	C							
Phenol, liquid - Alcohol Aromatic	C							
Phenol, pure - Alcohol, Aromatic	C							
Phenolates								
Phenolic Resins		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Phenylmercuric Acetate	B							
Phosphine	X							
Phospholeum								
Phosphoric Acid - 45%	A					X	B	B
Phosphoric Acid (<40%)	A	C				C	B	B
Phosphoric Acid (>40%)	A	X				X	B	B
Phosphoric Acid (40% -100% Solution)	A	B						
Phosphoric Acid (Crude)		C						
Phosphoric Acid (molten)	X	C						
Phosphoric Acid (to 40% Solution)	A	A						
Phosphoric Acid 20%	A	A					B	B
Phosphoric Acid 30%	A	A					B	B
Phosphoric Acid 50%	A	A					B	B
Phosphoric Acid 85%	A	A						
Phosphoric Acid- 1 and 5% - 70F and Boiling	A	A						
Phosphoric Acid- 1%	A	A						
Phosphoric Acid- 10% Aerated	A	A						
Phosphoric Acid- 10% Agitated	A	A						
Phosphoric Acid- 10% Boiling	A	A						
Phosphoric Acid- 10%- Still	A	A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Phosphoric Acid- 10% Still- 70F	A	A						
Phosphoric Acid- 15%	A	A		A	A			
Phosphoric Acid- 5%	A	A						
Phosphoric Acid- 50%	A	A		A	C			
Phosphoric Acid- 50%- 70F	A	A						
Phosphoric Acid- 50%- Boiling	A	A						
Phosphoric Acid- 50%aq. sol.-68F	A	A						
Phosphoric Acid- 80%	A	A		A	C			
Phosphoric Acid, 10%	A	A						
Phosphoric Acid, 25%	A	A						
Phosphoric Anhydride	A	A						
Phosphoric Anhydride (Dry or Moist)	A	A						
Phosphoric Anhydride (Molten)	X	A						
Phosphoric Anhydride- 68F	A	A						
Phosphoric Anhydride- Dry	A	A						
Phosphoric Oxychloride								
Phosphoric Trichloride						X	X	X
Phosphorous (Red)		A						
Phosphorous (Yellow)								
Phosphorous Pentoxide		A						

<u>A=Great Application;</u> <u>B=Good Application (mild</u> <u>effect); C=Conditional Use</u> <u>(consult with ES</u> <u>Technical Staff); X=Do</u> <u>Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Phosphorous Trichloride	B	A						
Phosphorous Trichloride Acid								
Phosphorus		A						
Phosphoryl Chloride								
Phosphorus Trichloride								
Phostphate Esters		A						
Photogen								
Photographic (Developer)	A	A						
Photographic Developers- 68F	A							
Photographic Emulsions- 68F	A							
Photographic Fixing Sol- 68F	A							
Photographic Hypo - Salt, Inorganic, Reducer	B							
Photographic Solutions	A	A						
Photoresists - Misc., Photoreist	X							
Phthalic Acid	A	A						
Phthalic Anhydride		B						
Picric Acid	A	A				B	A	A
Picric Acid- 1% w/w in water-68F	A					B		
Picric Acid- 10%	A	A				B		

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Picric Acid- 10% w/w in alcohol-68F	A	A				B		
Picric Acid- 70F	A	B				B		
Picric Acid- Concentrated	A	A				B		
Pine Oil	X	A				B	X	X
Pine Tar	X	A				B		
Pine Tar Oil	X	A				B		
Pine Tar Oil- Cold and Hot	X	B				B		
Pinene	X						B	B
Piperazine	X							
Piperidine	B					X	X	X
Piranha (H2SO4:H2O2) (70:30)	X							
Pitch								
Plating Solutions	A					A		
Plating Solutions (Brass)								
Plating Solutions (Cadmium)								
Plating Solutions (Chrome)		A						
Plating Solutions (Copper)								
Plating Solutions (Gold)								
Plating Solutions (Lead)								
Plating Solutions (Nickel)		A						
Plating Solutions (Rhodium)								
Plating Solutions (Silver)		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Potassium Acetate	A			A	A	B	B	B
Potassium Aluminum		A						
Potassium Aluminum Sulfate								
Potassium Aluminum Sulfate. Anhydrous								
Potassium Amyl Xanthate								
Potassium Antimonate	B							
Potassium Bicarbonate	B	B						
Potassium Bicarbonate-Sat'd.	B	A						
Potassium Bichromate-25%- 70F		B						
Potassium Bichromate-25%- Boiling		B						
Potassium Bichromate-Neutral		A						
Potassium Bichromate-Sat'd.		A						
Potassium Bisulfate		A						
Potassium Bisulphide-68F								
Potassium Bitartrate	B							
Potassium Borate		A						
Potassium Borate-68F								
Potassium Borates								
Potassium Bromate		A						
Potassium Bromide		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Potassium Bromide- 5%		A						
Potassium Bromide- 70F		B						
Potassium Carbonate	A	A						
Potassium Carbonate- 1%	A	A						
Potassium Carbonate- Solution- 70F and B	A	B						
Potassium Carbonate-68F	A							
Potassium Carbonate, Aq. Sat. - 70F	A	A						
Potassium Chlorate	A	A						
Potassium Chlorate (Aqueous)	A	A						
Potassium Chlorate- Saturated- Boiling		B						
Potassium Chloride	A	A	A	A	A	A	A	A
Potassium Chloride- 1% and 5%- 70F	A	B	A			A		
Potassium Chloride- 1% and 5%- Boiling	A	B	A			A		
Potassium Chloride- 1% to 5%	A	A	A			A		
Potassium Chloride- 1% to 5%- Boiling	A	A	A			A		
Potassium Chromate		B						
Potassium Chromic Sulfate								
Potassium Citrate	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Potassium Cuprocyanide-68F						A	A	A
Potassium Cyanate	B							
Potassium Cyanide	B	A				A	A	A
Potassium Cyanide Solutions		B						
Potassium Cyanide-68F								
Potassium Dichromate		A	A			A	A	A
Potassium Dichromate-All Concentrations		B	A			A	A	A
Potassium Dichromate-Neutral		A	A			A	A	A
Potassium Dichromate-Sta'd.		A	A			A	A	A
Potassium Dihydrogen Phosphate, pure - Salt, Inorganic	B							
Potassium Diphosphate	B							
Potassium Ferricyanide		A						
Potassium Ferricyanide-5%		A						
Potassium Ferricyanide-5% and 25%- Boiling		B						
Potassium Ferricyanide-5%- 70F		B						
Potassium Ferricyanide-70F		B						
Potassium Ferrocyanide		A						
Potassium Ferrocyanide-5%		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Potassium Ferrocyanide-68F								
Potassium Fluoride		A						
Potassium Fluoride-68F								
Potassium Glucocyanate	B							
Potassium Hydrate		A						
Potassium Hydroxide	A	B	A	A	A	A	A	A
Potassium Hydroxide - 25%	A	A	A			A	A	A
Potassium Hydroxide - 27%	A	A	A			A	A	A
Potassium Hydroxide (50%)	A/B	B	A	A	A	A	A	A
Potassium Hydroxide (Caustic Potash)	A	A	A	A	A	A	A	A
Potassium Hydroxide- 5%		A						
Potassium HydOrxide- 27% and 50%- Boiling		B						
Potassium Hydrxide- 5%- 70F		B						
Potassium Hypermanganate								
Potassium Hypochlorite		X						
Potassium Hypochlorite- 68F								
Potassium Iodate	B							
Potassium Iodide	A	A	A					
Potassium Iodide-All Concentrations- Col	A	B	A					
Potassium Metabisulfate	B							
Potassium Metachromate	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Potassium Metasilicate	X							
Potassium Monochromate	B							
Potassium Monosulfide								
Potassium Muriate								
Potassium Nitrate	A	A		A	A	A	A	A
Potassium Nitrate- 5%	A	A				A	A	A
Potassium Nitrate- 50%-70F	A	A				A	A	A
Potassium Nitrate- 50%-Boiling	A	A				A	A	A
Potassium Nitrate-68F	A	A				A	A	A
Potassium Nitrate, Aq. Sat.- 70F	A	A				A	A	A
Potassium Nitrite	A	A				A	A	A
Potassium Oxalate		B						
Potassium Perchlorate-68F								
Potassium Perfluoro Acetate	X							
Potassium Permanganate		A						
Potassium Permanganate- 10%		A						
Potassium Permanganate- 25%		A						
Potassium Permanganate- 5%- 70F		A						
Potassium Permanganate- 5%-Boiling		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect): C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Potassium Permanganate- Neutral		A						
Potassium Peroxide	X							
Potassium Pyrosulfate	B		A					
Potassium Salts	A							
Potassium Silicate								
Potassium Sodium Tartrate	B							
Potassium Stannate	B							
Potassium Stearate	B							
Potassium Sulfate	A	B		A	A	A	A	A
Potassium Sulfate, Aq. Sat.- 70F	A					A		
Potassium Sulfide	A	C				A	A	A
Potassium Sulfite	A	A				A	A	A
Potassium Sulphate	A							
Potassium Sulphate- 1% to 5%	A	A						
Potassium Sulphate- 1% to 5%- Hot	A	A						
Potassium Sulphate- 1%- 70F	A	A						
Potassium Sulphate- 5%- 70F	A	A						
Potassium Sulphate- 5%- Hot	A	A						
Potassium Sulphate-68F	A	A						
Potassium Sulphide (Salt)		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Potassium Sulphide-Solution- Hot		B						
Potassium Sulphide-68F								
Potassium Tartrate	B							
Potassium Thiocyanate	B							
Potassium Thiosulfate								
Potassium Thiosulphate-68F								
Potassium Triphosphate	B							
Potassium Tripolyphosphate		A						
Potato Oil								
Potato Spirit								
Power Steering Fluid 212F	C							
Power Steering Fluid 257F	X							
Power Steering Fluid 73F	A							
Prestone Antifreeze	A							
Propane	C/X	A				A	A	A
Propane (Liquified)	C/X	A						
Propane Nitrile								
Propane Propionitrile								
Propane- 100%		B	X					
Propanol	A	A						
Propionic Acid	A	A						
Propoinitrile	A							
Propyl		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Propyl Acetate	A	A					X	X
Propyl Acetone								
Propyl Alcohol	A	A					A	A
Propyl Alcohol (Propanol)	B	A						
Propyl Propionate	B							
Propylene	X	A				X	X	X
Propylene Aldehyde	A							
Propylene Chloride	C							
Propylene Chlorohydrin	X							
Propylene Diamine	B							
Propylene Dichloride								
Propylene Dichloride- 68F								
Propylene Glycol	A	B		A	A			
Propylene Glycol- 68F	A							
Propylene Imine	X							
Propylene Oxide	A	A					X	X
Pydrauls	A					X	X	X
Pyrex								
Pyridine	B	C	X			X	X	X
Pyridine (Oil)	B					X		
Pyridine Sulfate	B					X		
Pyridine Sulfonic Acid	B							
Pyridine, 5% - Amine, Heterocyclic	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Pyridine, 50% - Amine, Heterocyclic	B					X		
Pyrite								
Pyrrole						X		
Pyroacetic Spirit								
Pyroacetic Ether								
Pyrogallic Acid	X	B						
Pyrogallol Carboxylic Acid								
Pyrosulfuric Acid	B							
Pyrosulfuryl Chloride	C							
Pyroxylic Spirit								
Pyrrole		C					X	X
Pyruvic Acid	B							
Quaternary Ammonium Salts								
Quinidine	C							
Quinine	C							
Quinine Bisulphate (Dry)		B						
Quinine Hydrochloride	B							
Quinine Sulfate	B							
Quinine Sulphate (Dry)		B						
Quinine Tartrate	B							
Quinizarin	C							
Quinol								
Quinoline	C							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Quinone		A						
Radiation	A	A				C	B	B
Raffinate	C							
Ramrod - 2% aqueous	A							
Rapeseed Oil						B	B	B
Red Oil						A	B	B
Ref Fuel A (Isooctane)	A	A						
Ref Fuel B (Isooct/Tol 70/30)	B	A						
Ref Fuel C (Isooct/Tol 50/50)	B	A						
Resinoil								
Resorcinol	A							
Resorcinol, pure - Alcohol, Aromatic, Polyol	B							
Resorcinol, saturated - Alcohol, Aromatic, Polyol	B							
Retinol								
Rhigolene								
Rhodium	X							
Riboflavin	C							
Ricinoleic Acid	C							
Ricinus Oil (Ricinine)								
RJ-1 (MIL-F-82522)	C							
Rosin	C							
Rosin		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Rosin- Molten		B						
Rosins		A						
Roundup	A							
Roundup Super Concentrate	A							
Rubidium Bromide, pure - Salt, Inorganic	B							
Rubidium Chloride, pure - Salt, Inorganic	B							
Rum		A						
Rust Inhibitors		A						
Saccharin Solution	B							
Sal Ammoniac- 20%- Boiling	A	A				A	A	A
Salad Dressing		A	C					
Salicylic Acid	A	A		A	A	A		
Salicylic Acid- 68F	A					A		
Salt Brine	A	A	A			A		
Salt Brine (NaCl saturated)	A	A	A			A	A	A
Salt Water	A		A			A	A	A
Salt- Saturated		A	A					
Salt peter- Ammonium Nitrate	A	A						
Sauerkraut Brine- 70F		B						
Scott's Super Turf Builder	A							
SDS, pure - Detergent	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff);</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sea (Salt) Water	A		A				A	A
Sea Salt			A					
Sea Water	A	C/B	A				A	A
Sea Water- 70F	A	B/C	A			A	A	A
Sebacic Acid	B					A		
sec-Butanol, 100% - Alcohol, Aliphatic	B							
sec-Butanol, pure - Alcohol, Aliphatic	B							
sec-Butyl Alcohol, 100% - Alcohol, Aliphatic	B							
sec-Butyl Alcohol, pure - Alcohol, Aliphatic	B							
Selenous Acid	B							
Separan NP-10								
Sera - Misc.	B							
Serine-dl								
Sesame Oil								
Sesquicarbonate of Soda								
Sevin	A							
Sewage	A	B	A	A	A		A	A
Sewage (Sewerage)	A	B	A	A	A		A	A
SF 1147 GE Silicone Fluid	C							
SF 1154 GE Silicone Fluid	B							
SF96 GE Silicone Fluid	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Shale Naphtha								
Shell Alvania Grease #2								
Shell Lo Hydrax 27 and 29	C							
Shell Super Gas								
Shell Tellus #32 Pet. Base	C							
Shell Tellus #68	C							
Shell Tellus 27 (Petroleum Base)	C							
Shell Tellus 33	C							
Shellac (Bleached)		A						
Shellac (Orange)		A						
Sherwood Oil								
ShIPLEY AZ-111 Photoresist - Misc., Photoresist	X							
ShIPLEY AZ-1350 Photoresist - Misc., Photoresist	X							
ShIPLEY AZ-340 Photoresist - Misc., Photoresist	X							
Silane	X							
Silent Spirit								
Silicate Esters	A					B	A	A
Silicate of Soda	A							
Silicic Acid								
Silicofluoric Acid								
Silicon Fluoride	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Silicon Tetrachloride	X							
Silicon Tetrafluoride	X							
Silicone		A					A	A
Silicone Oil	A	A				A	A	A
Silver Bromide		C						
Silver Chloride		X						
Silver Cyanide		A						
Silver Cyanide- 68F								
Silver Nitrate	A	B		A	A	B	A	A
Silver Nitrate- 100%- 70F	A	B					A	A
Silver Nitrate- 100%- Boiling	A	B					A	A
Silver Plating 80-120F		A						
Silver Salts	A							
Skydrol 500	A						X	X
Skydrol 500-B4	A					X	X	X
Skydrol 7000	A					X	X	X
Skydrol LD-4	A					X		
Skydrol-500	A					X		
Slaked Lime								
Soap Solutions	A	A	A				A	A
Soap- 70F	A		A			A	A	A
Soaps	A	A	A			A	A	A
Soaps- 70F	A	A	A			A	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Soda Water	A	A	A			A		
Sodium Hydroxide- 10%	B	A				B		
Sodium (Molten)	X							
Sodium Acetate	A	A				B	B	B
Sodium Acetate (Moist)- 5%	A	A				B	B	B
Sodium Acetate- 68F	A	A				B	B	B
Sodium Acetate- Moist	A	A					B	B
Sodium Acetate- Sat'd.	A	A					B	B
Sodium Acetate, Powder							B	B
Sodium Acetate, Saturated							B	B
Sodium Acid Bisulfate	B							
Sodium Acid Carbonte								
Sodium Acid Fluoride	B							
Sodium Aluminate- Sat'd.	A	A		A	A	A		
Sodium Aluminum Sulfate								
Sodium Aluminum Sulfate, Saturated								
Sodium Anthraquinone Disulfate	B							
Sodium Antimonate	B							
Sodium Arsenate								
Sodium Arsenite	B							
Sodium Bicarbonate	A	A	A					
Sodium Bicarbonate (Baking Soda)	A	A	A				A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sodium Bicarbonate- 5%- 150F	A	A	A				A	A
Sodium Bicarbonate- 68F	A	A	A			A	A	A
Sodium Bicarbonate- All Conc.- 150 F	A	A	A			A	A	A
Sodium Bicarbonate- All Concentration- 7	A	A	A			A	A	A
Sodium Bichromate- Sat' d.	A	A	A					
Sodium Bichromate- Neutral	A	A	A					
Sodium Bifluoride	B							
Sodium Biphosphate	A							
Sodium Bisulfate	A	A				A	A	A
Sodium Bisulfide	A		A			A	A	A
Sodium Bisulfite	A	A	A	A	A	A	A	A
Sodium Bisulfite, 4%	A		A			A	A	A
Sodium Bisulfite, Saturated	A		A			A	A	A
Sodium Bisulphate	A	A	A			A	A	A
Sodium Bisulphate- 10% Boiling	A	A	A			A	A	A
Sodium Bisulphate- 10%- 70F	A	A	A			A	A	A
Sodium Bisulphite- 68F	A	A	A			A	A	A
Sodium Bitartrate	B						A	A
Sodium Borate	A	A				A	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sodium Borate (Borax)- Sat'd.	A	A				A	A	A
Sodium Borate- 68F	A					A	A	A
Sodium Borate- All Concentrations- Cold a	A	A				A	A	A
Sodium Bromide- 5%	A	A						
Sodium Bromide- 68F	A	A						
Sodium Bromide, Saturated	A	A						
Sodium Bromides	A	A						
Sodium Carbonate	A	B	A					
Sodium Carbonate (Soda Ash)	A		A					
Sodium carbonate- 5%- Boiling	A	B	A					
Sodium carbonate- 50% Boiling	A	B	A					
Sodium Carbonate- 68F	A		A					
Sodium Carbonate- All Conc.	A	A	A					
Sodium Carbonate- Molten- 1650F	X	C	X					
Sodium Chlorate	A	B	A					
Sodium Chlorate- 25%	A	A	A					
Sodium Chlorate- 68F	A		A					
Sodium Chlorate- Sat'd.	A	A	A					
Sodium chloride	A	B	A				A	A
Sodium Chloride Sulfate	A					A		

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sodium Chloride- 20% Aerated	A	B				A	A	A
Sodium Chloride- 25%- Cold and Hot	A	B				A		
Sodium Chloride- 5% Still- Room to 150F	A	B				A		
Sodium Chloride- 68F	A					A		
Sodium Chloride- All concentrations- 70F	A	B				A		
Sodium Chloride- Saturated	A	B				A		
Sodium Chloride- Saturated- 70F and Boiling		B				A		
Sodium Chloride- Saturated- Boiling		B				A		
Sodium Chloride, 3%	A	B				A		
Sodium Chloride, Aq. Sat. - 70F	A	B				A		
Sodium Chloride, Saturated	A	B				A		
Sodium Chlorite	A			A	A	A		
Sodium Chromate	A	A				A		
Sodium Citrate	A	A				A		
Sodium Citrate- All Concentrations- Cold a	A	B				A		
Sodium Cyanamide	B							
Sodium Cyanate	B							
Sodium Cyanide	A	A		A	A	A	A	A
Sodium Cyanide- 68F	A	A		A	A	A	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sodium Diacetate	B					A		
Sodium Dichromate	A		A					
Sodium Dichromate- 20%	A	A	A					
Sodium Dichromate, Saturated	A		A					
Sodium Dihydrogen Phosphate, pure - Salt, Inorganic	B							
Sodium Diphenyl Sulfonate	B							
Sodium Disilicate	B							
Sodium Disulfite								
Sodium Dodecyl Sulfate, pure - Detergent	B							
Sodium Ethylate	B							
Sodium Ferricyanide		A						
Sodium Ferricyanide- Sat' d.		A						
Sodium Ferrocyanide		B						
Sodium Ferrocyanide- Sat'd.		A						
Sodium Fluo Aluminate- 10%								
Sodium Fluoride		A						
Sodium Fluoride- 5%		B						
Sodium Fluorosilicate	B							
Sodium Glutamate	B							
Sodium Hydride	X							
Sodium Hydrogen Sulfate	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sodium Hydrosulfide	B							
Sodium Hydrosulfite								
Sodium Hydroxide (10%)	A	A	A			B	A	A
Sodium Hydroxide (20%)	A	A	A			B	A	A
Sodium Hydroxide (50% Solution)	A	B	B			B	A	A
Sodium Hydroxide (50%)	A	B	B			B	A	A
Sodium Hydroxide (80%)	A/B	B	C			B	A	A
Sodium Hydroxide (Caustic Soda)- 30%	A	A	A			B	A	A
Sodium Hydroxide 80% Solution	A/B	X	C			B	A	A
Sodium Hydroxide- 15%	A	A	A			B	A	A
Sodium Hydroxide- 20% and 30%- 70F	A	B	A			B	A	A
Sodium Hydroxide- 20%- Boiling	A	B	B					
Sodium Hydroxide- 30%- Boiling	A	B	B					
Sodium Hydroxide- 50%	A	A	B	A	A	A		
Sodium Hydroxide- 70%	A	A	C					
Sodium Hydroxide- Conc. - 68F								
Sodium Hydroxide- Molten- 650F		B						
Sodium Hypochlorite	A	A	A	A	A	A	B	B
Sodium Hypochlorite (<20%)	A	C	A	A	A	A	B	B

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff);</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sodium Hypochlorite (to 20%)	A	C	A	A	A	A	B	B
Sodium Hypochlorite- 5%	A	A	A	A	A	A	B	B
Sodium Hypophosphate	B							
Sodium Hypophosphite	B							
Sodium Hyposulfate		A						
Sodium Hyposulfite	B							
Sodium Hyposulphite- 70F		B						
Sodium Hyposulphite- Dilute		A						
Sodium Iodide	A							
Sodium Lactate		A						
Sodium Lauryl Sulfate, pure - Detergent	B							
Sodium Meta Phosphate		A					B	B
Sodium Metaphosphate- 68F							B	B
Sodium Metasilicate		A				A	B	B
Sodium Methylate	B					A	B	B
Sodium Monophosphate	B					A		
Sodium Nitrate	A	A	A			B	A	A
Sodium Nitrate- All Conc.	A	A	A			B	A	A
Sodium Nitrate- All Concentrations- Cold a	A	B	A			B	A	A
Sodium Nitrate- Sat'd.	A	A	A			B	A	A
Sodium Nitrite	A	A	A			B	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sodium Nitrite, Aq. Sat.- 70F	A	A	A			B	A	A
Sodium Oleate	B							
Sodium Orthosilicate	B							
Sodium Oxalate	B							
Sodium Perborate	A	C	A			B	B	B
Sodium Percarbonate	B							
Sodium Perchlorate- 10%- 70F	A	B						
Sodium Perchlorate- 10%- Boiling	A	B						
Sodium Peroxide	A	A					B	B
Sodium Peroxide- 10%- 70F	A	B				B	A	A
Sodium Peroxide- 10%- Boiling	A	B					A	A
Sodium Peroxide- 212F	A	A					B	B
Sodium Peroxide- 68F	A						B	B
Sodium Persulfate	B						A	A
Sodium Phenolate	B							
Sodium Phenoxide	B							
Sodium Phosphate	A		A	A	A	B	A	A
Sodium Phosphate (Dibasic)	A					A		
Sodium Phosphate (Mono)	A					A		
Sodium Phosphate (Tribasic)								
Sodium Phosphate- 5%	A	A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sodium Sulfate, Aq. Sat.- 70F								
Sodium Sulfide	A	B						
Sodium Sulfite	A	C						
Sodium Sulfite- 25% and 50%- Boiling	A	B						
Sodium Sulfite- 5%- 70F	A	B						
Sodium Sulfoyanide	B							
Sodium Sulphate	A		A			A	A	A
Sodium Sulphate- 5% 70F	A	B	A			A	A	A
Sodium Sulphate- 5% Still	A	A	A			A	A	A
Sodium Sulphate- 68F	A		A			A	A	A
Sodium Sulphate- Concentrated	A	A	A			A	A	A
Sodium Sulphate- Saturated- Boiling	A	B	A			A	A	A
Sodium Sulphide- 5%	A	A	A			A	A	A
Sodium Sulphide- 5%- 70F	A	B	A			A	A	A
Sodium Sulphide- 50%- Boiling	A	B	A			A	A	A
Sodium Sulphide- Saturated	A	A	A			A		
Sodium Tartrate	B					A		
Sodium Tetraborate		A						
Sodium Tetraphosphate	B							
Sodium Tetrasulfide	B							
Sodium Thioarsenate	B							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sodium Thiocyanate	B							
Sodium Thiosulfate	A		A				A	A
Sodium Thiosulphate	A	A	A				A	A
Sodium Thiosulphate ("Hypo")		A	A					
Sodium Thiosulphate- 25%- 70F		B	A					
Sodium Thiosulphate- 68F			A					
Sodium Thiosulphate- Acid Fixing Bath (H)		B						
Sodium Thiosulphate- Saturated- 70F and		B						
Sodium Trichloroacetate	B							
Solution 555, 20% - Misc.	X							
Solvesso 100, 150	X							
Sorbitol	B							
Sorghum		A						
Sour Crude Oil		A						
Sour Crude Oil (Contact Proco)								
Soy sauce		A						
Soybean Oil	B	A	C				B	B
Soybean Oil- 70F	B		C				B	B
Spectracide	A							
Stannic Ammonium Chloride	B							
Stannic Chloride	A	X	A				A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff);</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Stannic Chloride- 5%	A	X	A				A	A
Stannic Chloride- 50%	A		A				A	A
Stannic Chloride- 68F	A		A				A	A
Stannic Chloride- Sp. Gr. 1.21- 70F	A		A					
Stannic Chloride- Sp. Gr. 1.21- Boiling	A	C	A					
Stannic Fluoborate		A						
Stannic Sulfide	A							
Stannic Tetrachloride	B							
Stannous Bisulfate	B							
Stannous Bromide	B							
Stannous Chloride		C		A	A			
Stannous Chloride (15%)	B							
Stannous Chloride- 15%		A						
Stannous Chloride- 5%		B						
Stannous Chloride- 68F								
Stannous Chloride- Saturated- 120F		B						
Stannous Chloride- Saturated- Boiling		C						
Stannous Fluoride	B							
Stannous Sulfate	B							
Starch	A	A	A					
Starch Solution	A	A	A					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Steam	A	A				X	C	C
Steam (High Pressure)	A	A				X		
Steam (Low Pressure)	A	A				X		
Steam (Medium Pressure)	A	A				X		
Stearic Acid	A	A	A			B	B	B
Stearic Acid- 68F	A	A	A			B	B	B
Stearic Acid- 70F	A	A	A			B	B	B
Stearic Acid- Concentrated- 200F	B	A				B		
Stearic Acid-100%- 70F	A	A	A			B		
Stoddard Solvent	C	A				A	C	C
Storage Battery Acid- 70F	A		A					
Stripper S.A.								
Strontium Acetate	B							
Strontium Carbonate	B							
Strontium Chloride	B							
Strontium Hydroxide		B						
Strontium Nitrate Solution- Hot		B						
Styrene	C	A	X	C	C	X	X	X
Succinic Acid	A	A	A					
Sugar	A	A	A					
Sugar (Liquids)	A	A	A					
Sugar Juice	A	A	A					

<u>A=Great Application;</u> <u>B=Good Application (mild effect); C=Conditional Use (consult with ES Technical Staff); X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sugar Juice- Hot	A	B	A					
Sulfamic Acid- 20%	A	A						
Sulfamidic Acid	A							
Sulfanilic Acid	B							
Sulfanilic Chloride	C							
Sulfanilimide	C							
Sulfate Liquors	B	C				B	B	B
Sulfate Liquors (Oil)		A				B	B	B
Sulfite Cellulose Liquors								
Sulfite Liquors	B	A		A	A	B	B	B
Sulfonated Oils	C							
Sulfonic Acid	B							
Sulfonyl Chloride	B							
Sulfosalicylic Acid, pure - Acid, Organic, Aromatic	X							
Sulfur	A	A	A			X	A	A
Sulfur Chloride	B	X				C	C	C
Sulfur Dioxide	A	A	A			X	C	C
Sulfur Dioxide (Dry)	A	A				X	C	C
Sulfur Dioxide-Wet	A	A				X	C	C
Sulfur Salts, pure - Salt, Inorganic	C							
Sulfur Subchloride								
Sulfur Tetrafluoride	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sulfur Trioxide	A	C						
Sulfur Trioxide (Dry)	A	C						
Sulfuric Acid (<10%)	A	B				A	B	B
Sulfuric Acid (10%-75%)	A	X	X			A	B	B
Sulfuric Acid (20% Oleum)			A			A		
Sulfuric Acid (75%-100%)	A	X	X			A	B	B
Sulfuric Acid (Concentrated)	A		X			A	B	B
Sulfuric Acid (Dilute)	A		A			A	B	B
Sulfuric Acid (to 10%)	A	C	A			A	B	B
Sulfuric Acid 10%	A	C	A	A	A	A	B	B
Sulfuric Acid 10%-50%	A	X	C			A	B	B
Sulfuric Acid 50%-70%	A	X	X			A	B	B
Sulfuric Acid 70%-90%	A	X	X			C	B	B
Sulfuric Acid 98%	A	X	X	A	A	X	B	B
Sulfuric Acid Hot Concentrated	X	C	X			X	X	X
Sulfuric Acid- 10%- 70F	A		A			A	B	B
Sulfuric Acid- 25%- 70F	A		C			A	B	B
Sulfuric Acid- 50%- 70F	A		X			A	B	B
Sulfuric Acid- 60%	A	C	X			A	B	B
Sulfuric Acid- 70%	A	C	X			B/C	B	B
Sulfuric Acid- 80%	A	X	X			C	B	B
Sulfuric Acid- 90%	A	X	X			X	B	B
Sulfuric Acid- 93%	A	X	X			X	B	B

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sulfuric Acid- 94%	A	X	X			X	B	B
Sulfuric Acid- 95%	A	X	X			X	B	B
Sulfuric Acid- 96%	A	X	X			X	B	B
Sulfuric Acid- 96%- 70F	A		X			X	B	B
Sulfuric Acid- Cold Concentrated	B	B					X	X
Sulfuric Acid- Up to 30%	A	A	C			A	B	B
Sulfuric Acid-100%	A	C	X			A	B	B
Sulfuric Acid, 16%	A		B			A	B	B
Sulfuric Acid, 20%	A		C			A	B	B
Sulfuric Acid, 30%	A		C			A	B	B
Sulfuric Acid, 40%	A		C			A	B	B
Sulfuric Acid, 50%	A		X	A	A	A	B	B
Sulfuric Chlorohydrin (Chlorosulfonic Acid)	B							
Sulfuric Ether								
Sulfurous Acid	A	B					B	B
Sulfurous Acid 30%	A	B					B	B
Sulfurous Acid Anhydride								
Sulfurous Acid- Sat'd.		A						
Sulphur Chloride- Dry		X						
Sulphur Dioxide Gas- Dry- 575F		B						
Sulphur Dioxide Gas- Moist- 70F		B						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sulphur Dioxide- Dry		A						
Sulphur Dioxide- Dry-68F								
Sulphur Dioxide- Liquid- 68F								
Sulphur Dioxide- Moist		A						
Sulphur Dioxide- Moist- 68F								
Sulphur Monochloride- 70F		B						
Sulphur Trioxide- 68F	A					A		
Sulphur- Boiling- 830F		C						
Sulphur- Dry- Molten		A						
Sulphur- Fused- 265F		B						
Sulphur- Wet		X						
Sulphuric Acid- 10%	A	B				A	B	B
Sulphuric Acid- 10%- Boiling	A	X				X	B	B
Sulphuric Acid- 10%-70F	A	B					B	B
Sulphuric Acid- 5%	A	B				A	B	B
Sulphuric Acid- 5%- 70F	A	B				A	B	B
Sulphuric Acid- 5%- Boiling	A	X				X	B	B
Sulphuric Acid- 50%	A	X				A	B	B
Sulphuric Acid- 50%- 70F	A					A	B	B
Sulphuric Acid- 50%- Boiling	A	X				X		
Sulphuric Acid- 50%aq. sol.- 68F	A					A		
Sulphuric Acid- 60%aq. sol.- 68F	A					A		

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff);</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sulphuric Acid- 70%aq. sol.- 68F	A					B		
Sulphuric Acid- 80%aq. sol.- 68F	A					C		
Sulphuric Acid- 90%aq. sol.- 68F	A					X		
Sulphuric Acid- 95%aq. sol.- 68F	A					X		
Sulphuric Acid- 98%aq. sol.- 68F	A					X		
Sulphuric Acid- Conc.- 70F	X	X				X		
Sulphuric Acid- Conc.- Boiling	X	X				X		
Sulphuric Acid- Concentrated	X	X				X		
Sulphuric Acid- Concentrated- 300F	X	X				X		
Sulphuric Acid- Fuming	X	X				X		
Sulphuric Acid- Fuming- 70F	X	X				X		
Sulphuric Acid- Fuming- 68F	X					X		
Sulphuric Acid- Saturated- 70F	X	X				X		
Sulphurous Acid- 10%aq. sol.- 68F	A					B	B	B
Sulphurous Acid- 150#Pressure- 375F	X	B				X		
Sulphurous Acid- 30%aq. sol.- 68F	A					X		

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Sulphurous Acid-Saturated- 375F	B	B				B		
Sulphurous Spray		X						
Super Shell Gas	C							
Surfuryl Chloride	B							
sym-Trimethylbenzene, pure - Hydrocarbon, Aromatic	C							
Synthetic Blanc Fixe								
Syrup	A	A		A	A			
Tall Oil	B	A						
Tallol								
Tallow		A						
Tan								
Tannic Acid	A	A		A	A	A	A	A
Tannic Acid- 10%	A	A				A	A	A
Tannic Acid- 10%- 70F	A	A				A	A	A
Tannic Acid- 10%- Boiling	A	B				A		
Tannic Acid- 150F	A	A				A	A	A
Tannic Acid- 50%- 70F	A	B				A	A	A
Tannic Acid- 50%- Boiling	A	B				A	A	A
Tanning Extracts	A	A						
Tanning Extracts- 68F								
Tanning Liquor- 70F		B						
Tanning Liquors		A						

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Tanning Solutions								
Tap Water - Misc.	A		A					
Tar	X	B	C			B	C	C
Tartaric Acid	A	A	A			A	B	B
Tartaric Acid- 10%	A	A	A					
Tartaric Acid- 10%- 70F	A	B	A					
Tartaric Acid- 10%- Boiling	A	B	A					
Tartaric Acid- 150F	A	A	A					
Tartaric Acid- 50%- 70F	A	B	A					
Tartaric Acid- 50%- Boiling	A	B	A					
Taxaphene 12%								
TCA, 10% - Acid, Organic, Halogenated	B							
TCA, 100% - Acid, Organic, Halogenated	C							
TCA, 25% - Acid, Organic, Halogenated	C							
TCA, pure - Acid, Organic, Halogenated	C							
Tellone II	X							
Terebenthene								
Terebinthia								
Terephthalic Acid	B							
Terpenes								
Terpineol	C					B	X	X

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Tincture of Iodine - Misc.	B							
Titanic Acid	B							
Titanic Chloride	X					C		
Titanium Dioxide	B							
Titanium Sulfate	B							
Titanium Tetra Chloride	B	C		A	C			
Toilet Vinegar								
Tolit								
Toluene	C	A		A	A	X	X	X
Toluenesulfonic Acid	B							
Toluquinone	C							
Tolylaldehyde	B							
Tomato Juice	A	A	A			A		
Tomato Juice- 70F	A	A	A			A		
Transformer Oil	C	A	X			A	B	B
Transformer Oil- DTE/30	C	A	X			A		
Transmission Fluid Type A	C	A	X			A	B	B
Transmission Fluid-Automatic	C	A	X			A		
Triacetin						B	B	B
Tribasic Potassium Phosphate, pure - Salt, Inorganic	B							
Tributyl Phosphate	A	A				X	X	X

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Tributyl Phosphate-68F	A					X		
Trichlor Ethylene	C	A	X			X		
Trichloroacetic Acid-70F	A	C				B	B	B
Trichlorethylene Dry-70F	B	B				X	X	X
Trichloroacetic Acid	B	X				B	B	B
Trichloroacetic Acid-68F	B					B	B	B
Trichloroacetyl Chloride	C							
Trichloroethane	C	A	X					
Trichloroethane-68F	C		X					
Trichloroethanolamine	B							
Trichloroethylene	B	A	X			C	X	X
Trichlorofluoromethane pure - Hydrocarbon, Aliphatic, Halogenated	X							
Trichloromethane	C					X	X	X
Trichloronitromethane (Chloropicrin)	B							
Trichlorophenylsilane	X							
Trichloropropane		A						
Trichlorosilane	C							
Trichlorotrifluoroethane, pure - Hydrocarbon, Aliphatic, Halogenated	B							
Tricresyl Phosphate		A		A	A			
Tricresyl Phosphate-68F								
Triethanol Amine	C/X	A						

<u>A=Great Application;</u> <u>B=Good Application (mild</u> <u>effect); C=Conditional Use</u> <u>(consult with ES</u> <u>Technical Staff); X=Do</u> <u>Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Triethyl Aluminum								
Triethyl Amine		A		C	C			
Triethyl Borane								
Triethylamine	C/X	A						
Triethylene Glycol	A	A		A	A	B		
Trifluoroacetic Acid	B							
Trimethylbenzene	C							
Trimethylborate (TMB)	C							
Trimethylene Diamine								
Trimethylene Glycol								
Trimethylpentane	C							
Trios	C							
Trinitrotoluene	B						B	B
Tripoly Phosphate								
Tripostassium Phosphate, pure - Salt, Inorganic	B							
Tripotassium Phosphate	A							
Tripropylene Glycol								
Tripropylene Glycol Methyl Ether								
Tris Buffer Solution, pure - Misc.	B							
Trisodium Phosphate	A	A				X		
Trisodium Phosphate Dodecahydrate	A	A				X		

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Trisopropylbenzylchloride	C							
Tritium	X							
Tritolyl Phosphate								
Triton								
Trotyl								
Tryptophan-dl (Powder)								
TSP, pure - Base/Caustic, Inorganic	B							
Tung Oil	X	A					B	B
Tung Oil (China Wood Oil)	X	A				A		
Tung Oil-Cold and Hot	X	A				A		
Tungsten Hexafluoride	X					A		
Tungstic Acid	X					A		
Turbine Oil	X					B	B	B
Turbine Oil-#15 (MIL-L- 7808)	X					B		
Turbo Oil-#35	X					B		
Turkey Red Oil								
Turpentine	C	A	X	A	A		X	X
Turpentine Oil	C	A	X					
Turpentine Substitute								
Turpentine-68F								
Turpentine-70F		B						
Undecylenic Acid	C							
Undecylic Acid	C							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
UPDI (Ultrapure Deionized Water)	B		A					
Uran								
Uranium Hexachloride	X							
Uranium Hexafluoride	X							
Uranium Sulfate	X							
Urea	A	B	A			A		
Urea-68F	A	B	A			A		
Urea, Aq. Sat. -70F	A	B	A			A		
Uric Acid	A	B						
Uric Acid- Concentrated	A	A						
Uric Acid-70F	A	B						
Urine	A	A	A					
V.M. & P. Naphtha								
Valeraldehyde	B							
Valerianic Acid								
Valeric Acid	B							
Valerone								
Valine-dl (Powder)								
Vamish	X	A				B	C	C
Vanadium Oxide	C							
Vanadium Pentoxide	C							
Vanilla Extract								
Varnish	X	A				B	C	C

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Wagner 21B Fluid						C	A	A
Water	A	A	A	A	A	A	A	A
Water (Brine)	A	A	A	A	A	A	A	A
Water (DI)	A	A	A	A	A	A	A	A
Water (Steam)	A	A	A	A	A	A	A	A
Water Distilled. Lab. Ret. Cond.	A	A	A	A	A	A	A	A
Water Glass	A	A	A	A	A	A	A	A
Water Proofing Salt	A	A	A	A	A	A	A	A
Water-68F	A	A	A	A	A	A	A	A
Water-Deionized	A	A	A	A	A	A	A	A
Water-Drinking	A	A	A	A	A	A	A	A
Water-Fresh	A	A	A	A	A	A	A	A
Water-Heavy	A	A	A	A	A	A	A	A
Water-Hot	A	A	A	A	A	A	A	A
Water-Seawater/River Water	A	B	A	A	A	A	A	A
Water, Acid, Mine	A	A	X	A	A	A	A	A
Water, Deionized	A	A	A	A	A	A	A	A
Water, Distilled	A	A	A	A	A	A	A	A
Water, Distilled, Lab Grade 7	A	A	A	A	A	A	A	A
Water, Fresh	A	A	A	A	A	A	A	A
Water, Potable	A	A	A	A	A	A	A	A
Water, Salt	A	C	A	A	A	A	A	A
Water, Sea	A	C	A	A	A	A	A	A

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Water, Soft	A	A	A	A	A	A	A	A
Water, Waste	A	A	A	A	A	A	A	A
Wax								
Waycoat 59 Photoresist - Misc., Photoresist	X							
Weed Killers	A	A						
Whey		A						
Whiskey	A	B				A	A	A
Whiskey and Wines	A	A				A	A	A
White Liquor		A	X	A	A			
White Liquor (Pulp Mill)		A	X					
White Paraffin, pure - Hydrocarbon, Mixture	C		X					
White Pine Oil	X		X			B	X	X
White Spirits - Hydrocarbon, Mixture	X						B	B
White Water (Paper Mill)		A						
Whitening								
Whiting								
Wine	A	A	A					
Wood Oil	X					A	B	B
Wort		B						
Xylene	C	A	X				X	X
Xylene (Xylil)	C	A	X					

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Zephiran Chloride, 1% - Misc., Disinfectant	B							
Zephiran Chloride, 7% - Misc., Disinfectant	B							
Zephrian Chloride (Benzalkonium Chloride)								
Zinc Acetate	A	A				B	B	B
Zinc Ammonium Chloride	B						A	A
Zinc Bromide	A	C						
Zinc Butter								
Zinc Carbonate	A	C						
Zinc Chloride	A	C				A	A	A
Zinc Chloride-20%-70F	A	B				A	A	A
Zinc Chloride-20%-Boiling	A	B				A	A	A
Zinc Chloride-5%-70F	A	B				A	A	A
Zinc Chloride-5%-Boiling	A	B				A	A	A
Zinc Chloride-5%Still	A	B				A	A	A
Zinc Chloride-5%Still-Boiling	A	B				A	A	A
Zinc Chloride-70%-70F	A	B				A	A	A
Zinc Chloride-70%-Boiling	A	B				A	A	A
Zinc Cyanide-Moist-70F		B						
Zinc Diethyldithiocarbamate	B							
Zinc Dihydrogen Phosphate	B							
Zinc Fluorosilicate	X							

<u>A=Great Application:</u> <u>B=Good Application (mild effect):</u> <u>C=Conditional Use (consult with ES Technical Staff):</u> <u>X=Do Not Use</u>	Earth Shield® TPV Waterstop	Earth Shield® 316L Stainless Steel Waterstop	Earth Shield® Flexible PVC Waterstop	Earth Shield® VEN1000 Novolac Epoxy	Earth Shield® VEN500 Novolac Epoxy	Earth Shield® Type 125CR Mastic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Strip Applied Waterstop	Earth Shield® Type NB190® Hydrophilic Waterstop Paste
Zinc Hydrosulfite		A						
Zinc Hydrosulfite (10%)								
Zinc Hydrosulphite		A						
Zinc Nitrate		A						
Zinc Nitrate-Sol. Hot		B						
Zinc Oxide								
Zinc Oxide Ointment								
Zinc Oxide, Saturated								
Zinc Plating, Acid Chloride 140F	A	X						
Zinc Plating, Acid Fluoborate Bath R.T		C						
Zinc Plating, Alkaline Cyanide Bath R.T		A						
Zinc Plating,Acid Sulfate Bath 150F		C						
Zinc Salts	A		A					
Zinc Silicate, Native								
Zinc Stearate								
Zinc Sulfate	A	A				A	A	A
Zinc Sulfate-Heptahydrate								
Zinc Sulfate, Saturated								
Zinc Sulfide	B							
Zinc Sulphate								
Zinc Sulphate-25%- Boiling		B						

